

APPROVAL SHEET

MULTILAYER CERAMIC CAPACITORS

General Purpose Series (4V to 100V)

0201 to 1812 Sizes

NP0, X7R, Y5V, X6S & X5R Dielectrics

RoHS Compliance

*Contents in this sheet are subject to change without prior notice.

1. DESCRIPTION

MLCC consists of a conducting material and electrodes. To manufacture a chip-type SMT and achieve miniaturization, high density and high efficiency, ceramic condensers are used.

WTC's MLCC is made by NP0, X7R, X6S, X5R and Y5V dielectric material and which provides product with high electrical precision, stability and reliability.

2. FEATURES

- a. A wide selection of sizes is available (0201 to 1812).
- b. High capacitance in given case size.
- c. Capacitor with lead-free termination (pure Tin).

3. APPLICATIONS

- a. For general digital circuit.
- b. For power supply bypass capacitors.
- c. For consumer electronics.
- d. For telecommunication.

4. HOW TO ORDER

1206	B	104	K	500	C	I
Size	Dielectric	Capacitance	Tolerance	Rated voltage	Termination	Packaging style
Inch (mm)						
0201 (0603)	N=NP0 (C0G)	Two significant digits followed by	A=±0.05pF	Two significant digits followed by		
0402 (1005)	B=X7R	no. of zeros. And	B=±0.1pF	no. of zeros. And		
0603 (1608)	F=Y5V	R is in place of	C=±0.25pF	R is in place of		
0805 (2012)	X=X5R	decimal point.	D=±0.5pF	decimal point.		
1206 (3216)	S=X6S		F=±1%			
1210 (3225)		eg.: 0R5=0.5pF	G=±2%	4R0=4 VDC		
1812 (4532)		1R0=1.0pF	J=±5%	6R3=6.3 VDC		
		104=10x10 ⁴	K=±10%	100=10 VDC		
		=100nF	M=±20%	160=16 VDC		
			Z=−20/+80%	250=25 VDC		
				500=50 VDC		
				101=100 VDC		
					C=Cu/Ni/Sn	
						T=7" reeled
						R=7" reeled (2mm pitch for 0603 size; paper tape)
						G=13" reeled

5. EXTERNAL DIMENSIONS

Outline	Size Inch (mm)	L (mm)	W (mm)	T (mm)/Symbol	Soldering Method *	M _B (mm)
<p>Fig. 1 The outline of MLCC</p>	01R5 (0402)	0.4±0.02	0.2±0.02	0.2±0.02	V	0.10±0.03
	0201 (0603)	0.6±0.03	0.3±0.03	0.3±0.03	L	0.15±0.05
		0.6±0.05 ^{#2}	0.3±0.05 ^{#2}	0.3±0.05 ^{#2}		
		0.6±0.09 ^{#3}	0.3±0.09 ^{#3}	0.3±0.09 ^{#3}		0.15+0.1/-0.05
	0402 (1005)	1.00±0.05	0.50±0.05	0.50±0.05	N	0.25 +0.05/-0.10
				0.50+0.02/-0.05	Q	
		1.00±0.20	0.50±0.20	0.5±0.20	E	
	0603 (1608)	1.60±0.10	0.80±0.10	0.80±0.07	S	R / W 0.40±0.15
		1.60+0.15/-0.10	0.80+0.15/-0.10	0.50±0.10	H	
				0.80+0.15/-0.10	X	
	0805 (2012)	1.60±0.20 ^{#1}	0.80±0.20 ^{#1}	0.8±0.20 ^{#1}		
		2.00±0.15	1.25±0.10	0.50±0.10	H	R / W 0.50±0.20
				0.60±0.10	A	
				0.80±0.10	B	
		2.00±0.20	1.25±0.20	1.25±0.10	D	R (0.5±0.25)***
				0.85±0.10 ^{#4}	T ^{#4}	
				1.25±0.20	I	
	1206 (3216)	3.20±0.15	1.60±0.15	0.80±0.10	B	R / W 0.60±0.20 (0.5±0.25)***
				0.95±0.10	C	
				1.25±0.10	D	
		3.20±0.20	1.60±0.20	1.15±0.15	J	
				1.60±0.20	G	
				0.85±0.10	T	
				1.60+0.30/-0.10	P	
	1210 (3225)	3.20±0.30	2.50±0.20	0.95±0.10	C	R 0.75±0.25
				0.85±0.10	T	
				1.25±0.10	D	
		3.20±0.40	2.50±0.30	1.60±0.20	G	
				2.00±0.20	K	
				2.50±0.30	M	
	1808 (4520)	4.50±0.40 (4.5+0.5/-0.3)**	2.03±0.25	1.25±0.10	D	R 0.75±0.25 (0.5±0.25)***
				1.40±0.15	F	
				1.60±0.20	G	
				2.00±0.20	K	
	1812 (4532)	4.50±0.40 (4.5+0.5/-0.3)**	3.20±0.30	1.25±0.10	D	R 0.75±0.25 (0.5±0.25)***
				1.60±0.20	G	
				2.00±0.20	K	
				2.50±0.30	M	
		3.20±0.40	3.20±0.40	2.50±0.30	U	
				2.80±0.30	R	

* R = Reflow soldering process ; W = Wave soldering process.

** For 1808_200V~3kV, 1812_200V~3kV and safety certificated products.

*** For 1206_1000V~3kV, 1808_200V~3kV, 1812_200V~3kV and safety certificated products.

#1 : For 0603/Cap≥10μF or 0603(>10V)/Cap>1μF products.

#2 : For 0201/Cap≥0.68μF products.

#3 : For 0201/Cap≥1μF products.

#4 : For 0805/0.22μF/100V/ T thickness:0.85+0.15/-0.1(mm)

6. GENERAL ELECTRICAL DATA

Dielectric	NP0	X7R	Y5V	X5R	X6S
Size	0402, 0603, 0805, 1206, 1210, 1812				
Capacitance range*	0.1pF to 0.1μF	100pF to 47μF	0.01μF to 100μF	100pF to 220μF	0.1μF to 100μF
Capacitance tolerance**	Cap≤5pF ^{#1} : A (±0.05pF), B (±0.1pF), C (±0.25pF) 5pF<Cap<10pF: C (±0.25pF), D (±0.5pF) Cap≥10pF: F (±1%), G (±2%), J (±5%), K (±10%)	J (±5%), K (±10%), M (±20%)	M (±20%), Z (-20/+80%)	K (±10%), M (±20%)	K (±10%), M (±20%)
Rated voltage (WVDC)	10V, 16V, 25V, 50V, 100V	6.3V, 10V, 16V, 25V, 50V, 100V	4V, 6.3V, 10V, 16V, 25V, 50V		
DF(Tan δ)*	Cap<30pF: Q≥400+20C Cap≥30pF: Q≥1000	Note 1			
Operating temperature	-55 to +125°C		-25 to +85°C	-55 to +85°C	-55 to +105°C
Capacitance characteristic	±30ppm	±15%	+30/-80%	±15%	±22%
Termination	Ni/Sn (lead-free termination)				

#1: NP0, 0.1pF product only provide B tolerance; 0603N0R4 provide B&C tolerance; 0603N0R3 only provide C tolerance.

* Measured at the condition of 30~70% related humidity.

NP0: Apply 1.0±0.2Vrms, 1.0MHz±10% for Cap≤1000pF and 1.0±0.2Vrms, 1.0kHz±10% for Cap>1000pF, 25°C at ambient temperature
X7R/X6S/X5R: Apply 1.0±0.2Vrms, 1.0kHz±10%, at 25°C ambient temperature.

Y5V: Apply 1.0±0.2Vrms, 1.0kHz±10%, at 20°C ambient temperature.

** Preconditioning for Class II MLCC: Perform a heat treatment at 150±10°C for 1 hour, then leave in ambient condition for 24±2 hours before measurement.

Note 1:

X7R/X5R/X6S

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥ 100V	≤ 2.5%	≤ 3% 1206 ≥ 0.47μF
		≤ 5% 0805 > 0.1μF, 0603 ≥ 0.068μF, 1206 > 1μF; TT series
50V	≤ 2.5%	≤ 3% 0201(50V); 0603 ≥ 0.047μF; 0805 ≥ 0.18μF; 1206 ≥ 0.47μF
		≤ 5% 1210 ≥ 4.7μF
		≤ 10% 0402 ≥ 0.1μF; 0603 > 0.1μF; 0805 ≥ 1μF; 1206 ≥ 2.2μF; 1210 ≥ 10μF; TT series
35V	≤ 3.5%	≤ 10% 0603 ≥ 1μF; 0805 ≥ 2.2μF; 1210 ≥ 10μF
25V	≤ 3.5%	≤ 5% 0201 ≥ 0.01μF; 0805 ≥ 1μF; 1210 ≥ 10μF
		≤ 7% 0603 ≥ 0.33μF; 1206 ≥ 4.7μF
		≤ 10% 0402 ≥ 0.10μF; 0603 ≥ 0.47μF; 0805 ≥ 2.2μF; 1206 ≥ 6.8μF; 1210 ≥ 22μF; TT series
		≤ 12.5% 0402 ≥ 1μF
16V	≤ 3.5%	≤ 5% 0201 ≥ 0.01μF; 0402 ≥ 0.033μF; 0603 ≥ 0.15μF; 0805 ≥ 0.68μF; 1206 ≥ 2.2μF; 1210 ≥ 4.7μF
		≤ 10% 0201 ≥ 0.1μF; 0402 ≥ 0.22μF; 0603 ≥ 0.68μF; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF; TT series
10V	≤ 5%	≤ 10% 0201 ≥ 0.012μF; 0402 ≥ 0.33μF(0402/X7R ≥ 0.22μF); TT series 0603 ≥ 0.33μF; 0805 ≥ 2.2μF; 1206 ≥ 2.2μF; 1210 ≥ 22μF
		≤ 15% 0201 ≥ 0.1μF; 0402 ≥ 1μF
		≤ 15% 0201 ≥ 0.1μF; 0402 ≥ 1μF; 0603 ≥ 10μF; 0805 ≥ 4.7μF; 1206 ≥ 47μF; 1210 ≥ 100μF; TT series
6.3V	≤ 10%	≤ 20% 0402 ≥ 2.2μF
4V	≤ 15%	---

Y5V

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥ 50V	5%	7% 0603 ≥ 0.1μF; 0805 ≥ 0.47μF; 1206 ≥ 4.7μF
35V	7%	---
25V	5%	0402 ≥ 0.047μF; 0603 ≥ 0.1μF; 0805 ≥ 0.33μF; 1206 ≥ 1μF; 1210 ≥ 4.7μF
		0402 ≥ 0.068μF; 0603 ≥ 0.47μF; 1206 ≥ 4.7μF; 1210 ≥ 22μF
16V (C < 1.0μF)	7%	9% 0402 ≥ 0.068μF; 0603 ≥ 0.68μF
		12.5% 0402 ≥ 0.22μF
16V (C ≥ 1.0μF)	9%	12.5% 0603 ≥ 2.2μF; 0805 ≥ 3.3μF; 1206 ≥ 10μF; 1210 ≥ 22μF; 1812 ≥ 47μF
		10V 12.5% 20% 0402 ≥ 0.47μF
6.3V	20%	---

7. CAPACITANCE RANGE

7-1. NP0 Dielectric 0201, 0402, 0603, 0805 Sizes

DIELECTRIC SIZE RATED VOLTAGE (VDC)	NP0																	
	0201			0402				0603				0805						
	16	25	50	10	16	25	50	100	10	16	25	50	100	10	16	25	50	100
0.1pF (0R1)	L	L	L	N	N	N	N											
0.2pF (0R2)	L	L	L	N	N	N	N											
0.3pF (0R3)	L	L	L	N	N	N	N		S	S	S	S						
0.4pF (0R4)	L	L	L	N	N	N	N		S	S	S	S						
0.5pF (0R5)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
0.6pF (0R6)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
0.7pF (0R7)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
0.8pF (0R8)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
0.9pF (0R9)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
1.0pF (1R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
1.2pF (1R2)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
1.5pF (1R5)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
1.8pF (1R8)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
2.0pF (2R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
2.2pF (2R2)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
2.7pF (2R7)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
3.0pF (3R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
3.3pF (3R3)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
3.9pF (3R9)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
4.0pF (4R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
4.7pF (4R7)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
5.0pF (5R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
5.6pF (5R6)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
6.0pF (6R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
6.8pF (6R8)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
7.0pF (7R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
8.0pF (8R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
8.2pF (8R2)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
9.0pF (9R0)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
10pF (100)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
12pF (120)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
15pF (150)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
18pF (180)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
22pF (220)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
27pF (270)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
33pF (330)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
39pF (390)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
47pF (470)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
56pF (560)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
68pF (680)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
82pF (820)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
100pF (101)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
120pF (121)	L	L	L	N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
150pF (151)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
180pF (181)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
220pF (221)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
270pF (271)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
330pF (331)				N	N	N	N	N	S	S	S	S	S	A	A	A	A	A
390pF (391)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
470pF (471)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
560pF (561)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
680pF (681)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
820pF (821)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
1,000pF (102)				N	N	N	N	N	S	S	S	S	S	B	B	B	B	B
1,200pF (122)									X	X	X	X	X	B	B	B	B	B
1,500pF (152)									X	X	X	X	X	B	B	B	B	B
1,800pF (182)									X	X	X	X	X	B	B	B	B	B
2,200pF (222)									X	X	X	X	X	B	B	B	B	B
2,700pF (272)									X	X	X	X	X	D	D	D	D	D
3,300pF (332)									X	X	X	X	X	D	D	D	D	D
3,900pF (392)									X	X	X	X	X	D	D	D	D	D
4,700pF (472)									X	X	X	X	X	D	D	D	D	D
5,600pF (562)									X	X	X	X	X	D	D	D	D	D
6,800pF (682)									X	X	X	X	X	D	D	D	D	D
8,200pF (822)									X	X	X	X	X	D	D	D	D	D
0.010uF (103)									X	X	X	X	X	D	D	D	D	D
0.012uF (123)														T	T	T	T	
0.018uF (183)														D	D	D	D	
0.022uF (223)														D	D	D	D	

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

7-1. NP0 Dielectric 1206, 1210, 1812 Sizes

DIELECTRIC SIZE		NP0												
		1206					1210				1812			
RATED VOLTAGE (VDC)		10	16	25	50	100	10	16	25	50	100	16	50	100
Capacitance	1.0pF (1R0)													
	1.2pF (1R2)	B	B	B	B	B								
	1.5pF (1R5)	B	B	B	B	B								
	1.8pF (1R8)	B	B	B	B	B								
	2.2pF (2R2)	B	B	B	B	B								
	2.7pF (2R7)	B	B	B	B	B								
	3.3pF (3R3)	B	B	B	B	B								
	3.9pF (3R9)	B	B	B	B	B								
	4.7pF (4R7)	B	B	B	B	B								
	5.6pF (5R6)	B	B	B	B	B								
	6.8pF (6R8)	B	B	B	B	B								
	8.2pF (8R2)	B	B	B	B	B								
	10pF (100)	B	B	B	B	B	C	C	C	C	C	D	D	
	12pF (120)	B	B	B	B	B	C	C	C	C	C	D	D	
	15pF (150)	B	B	B	B	B	C	C	C	C	C	D	D	
	18pF (180)	B	B	B	B	B	C	C	C	C	C	D	D	
	22pF (220)	B	B	B	B	B	C	C	C	C	C	D	D	
	27pF (270)	B	B	B	B	B	C	C	C	C	C	D	D	
	33pF (330)	B	B	B	B	B	C	C	C	C	C	D	D	
	39pF (390)	B	B	B	B	B	C	C	C	C	C	D	D	
	47pF (470)	B	B	B	B	B	C	C	C	C	C	D	D	
	56pF (560)	B	B	B	B	B	C	C	C	C	C	D	D	
	68pF (680)	B	B	B	B	B	C	C	C	C	C	D	D	
	82pF (820)	B	B	B	B	B	C	C	C	C	C	D	D	
	100pF (101)	B	B	B	B	B	C	C	C	C	C	D	D	
	120pF (121)	B	B	B	B	B	C	C	C	C	C	D	D	
	150pF (151)	B	B	B	B	B	C	C	C	C	C	D	D	
	180pF (181)	B	B	B	B	B	C	C	C	C	C	D	D	
	220pF (221)	B	B	B	B	B	C	C	C	C	C	D	D	
	270pF (271)	B	B	B	B	B	C	C	C	C	C	D	D	
	330pF (331)	B	B	B	B	B	C	C	C	C	C	D	D	
	390pF (391)	B	B	B	B	B	C	C	C	C	C	D	D	
	470pF (471)	B	B	B	B	B	C	C	C	C	C	D	D	
	560pF (561)	B	B	B	B	B	C	C	C	C	C	D	D	
	680pF (681)	B	B	B	B	B	C	C	C	C	C	D	D	
	820pF (821)	B	B	B	B	B	C	C	C	C	C	D	D	
	1,000pF (102)	B	B	B	B	B	C	C	C	C	C	D	D	
	1,200pF (122)	B	B	B	B	B	C	C	C	C	C	D	D	
	1,500pF (152)	B	B	B	B	B	C	C	C	C	C	D	D	
	1,800pF (182)	B	B	B	B	B	C	C	C	C	C	D	D	
	2,200pF (222)	B	B	B	B	B	C	C	C	C	C	D	D	
	2,700pF (272)	B	B	B	B	B	C	C	C	C	C	D	D	
	3,300pF (332)	B	B	B	B	B	C	C	C	C	C	D	D	
	3,900pF (392)	B	B	B	B	B	C	C	C	C	C	D	D	
	4,700pF (472)	B	B	B	B	B	C	C	C	C	C	D	D	
	5,600pF (562)	B	B	B	B	B	C	C	C	C	C	D	D	
	6,800pF (682)	C	C	C	C	C	C	C	C	C	C	D	D	
	8,200pF (822)	D	D	D	D	D	C	C	C	C	C	D	D	
	0.010μF (103)	D	D	D	D	D	C	C	C	C	C	D	D	
	0.012μF (123)	T	T	T	T	T	D	D	D	D	D	D	D	
	0.015μF (153)	T	T	T	T	T	D	D	D	D	D	D	D	
	0.018μF (183)	T	T	T	T	T						D	D	
	0.022μF (223)	T	T	T	T	T						D	D	
	0.027μF (273)	T	T	T	T	T						D	D	
	0.033μF (333)	T	T	T	T	T						D	D	
	0.039μF (393)	J	J	J	J	J								
	0.047μF (473)	J	J	J	J	J								
	0.056μF (563)	J	J	J	J	J								
	0.068μF (683)	G	G	G	G	G								
	0.082μF (823)	G	G	G	G	G								
	0.1μF (104)	G	G	G	G	G								

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

7-2. X7R Dielectric 0201, 0402, 0603, 0805 Sizes

DIELECTRIC		X7R																								
SIZE		0201					0402					0603					0805									
RATED VOLTAGE (VDC)		6.3	10	16	25	50	6.3	10	16	25	50	100	6.3	10	16	25	50	100	6.3	10	16	25	50	100		
Capacitance	100pF (101)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	120pF (121)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	150pF (151)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	180pF (181)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	220pF (221)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	270pF (271)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	330pF (331)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	390pF (391)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	470pF (471)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	560pF (561)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	680pF (681)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	820pF (821)		L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	1,000pF (102)	L	L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	1,200pF (122)	L	L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	1,500pF (152)	L	L	L	L		N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	1,800pF (182)	L	L	L			N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	2,200pF (222)	L	L	L			N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	2,700pF (272)	L	L	L			N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	3,300pF (332)	L	L	L			N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	3,900pF (392)	L	L	L			N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	4,700pF (472)	L	L	L			N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	5,600pF (562)	L	L				N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	6,800pF (682)	L	L				N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	8,200pF (822)	L	L				N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	0.010μF (103)	L	L	L			N	N	N	N	N	N	S	S	S	S	S	S	B	B	B	B	B	B		
	0.012μF (123)						N	N	N				S	S	S	S	X		B	B	B	B	B	B		
	0.015μF (153)						N	N	N				S	S	S	S	X		B	B	B	B	B	B		
	0.018μF (183)						N	N	N				S	S	S	S	X		B	B	B	B	B	B		
	0.022μF (223)						N	N	N	N			S	S	S	S	X		B	B	B	B	B	B		
	0.027μF (273)						N	N	N				S	S	S	S	X		B	B	B	D				
	0.033μF (333)						N	N	N	N			S	S	S	X	X		B	B	B	D				
	0.039μF (393)						N	N	N				S	S	S	X	X		B	B	B	D				
	0.047μF (473)						N	N	N	N			S	S	S	X	X		B	B	B	D				
	0.056μF (563)						N	N					S	S	S	X	X		B	B	B	D				
	0.068μF (683)							N	N	N			S	S	S	X	X		B	B	B	B	D			
	0.082μF (823)							N	N				S	S	S	X	X		B	B	B	B	D			
	0.10μF (104)						N	N	N	N	N		S	S	S	X	X		B	B	B	B	D			
	0.12μF (124)												S	S	X				B	B	B	D				
	0.15μF (154)												S	S	X				D	D	D	D				
	0.18μF (184)												S	S	X				D	D	D	D				
	0.22μF (224)						N	N	N	N			S	S	X	X			D	D	D	D	T			
	0.27μF (274)												X	X	X	X			D	D	D	I				
	0.33μF (334)												X	X	X	X			D	D	D	I				
	0.39μF (394)												X	X	X	X			D	D	D	I				
	0.47μF (474)						N	N					X	X	X	X	X		D	D	D	I	I			
	0.56μF (564)												X	X	X				D	D	D	D				
	0.68μF (684)												X	X	X				D	D	D	D				
	0.82μF (824)												X	X	X				D	D	D	D				
	1.0μF (105)						N						X	X	X	X	X		D	D	D	I				
	1.5μF (155)																		I	I	I					
	2.2μF (225)												X	X	X				I	I	I	I	I			
	3.3μF (335)																									
	4.7μF (475)																		I	I	I	I	I			
	6.8μF (685)																									
	10μF (106)																		I	I	I*					
	22μF (226)																									

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “*” mark is expressed product not in 10% (code “K”) tolerance.

7-2. X7R Dielectric 1206, 1210, 1812 Sizes

DIELECTRIC		X7R															
SIZE		1206					1210					1812					
RATED VOLTAGE (VDC)	6.3	10	16	25	50	100	6.3	10	16	25	50	100	10	16	25	50	100
100pF (101)																	
120pF (121)																	
150pF (151)	B	B	B	B	B												
180pF (181)	B	B	B	B	B												
220pF (221)	B	B	B	B	B												
270pF (271)	B	B	B	B	B												
330pF (331)	B	B	B	B	B												
390pF (391)	B	B	B	B	B												
470pF (471)	B	B	B	B	B												
560pF (561)	B	B	B	B	B												
680pF (681)	B	B	B	B	B												
820pF (821)	B	B	B	B	B												
1,000pF (102)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
1,200pF (122)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
1,500pF (152)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
1,800pF (182)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
2,200pF (222)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
2,700pF (272)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
3,300pF (332)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
3,900pF (392)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
4,700pF (472)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
5,600pF (562)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
6,800pF (682)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
8,200pF (822)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.010μF (103)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.012μF (123)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.015μF (153)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.018μF (183)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.022μF (223)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.027μF (273)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.033μF (333)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.039μF (393)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.047μF (473)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.056μF (563)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.068μF (683)	B	B	B	B	B		C	C	C	C	C	D	D	D	D	D	D
0.082μF (823)	B	B	B	B	D		C	C	C	C	C	D	D	D	D	D	D
0.10μF (104)	B	B	B	B	D		C	C	C	C	C	D	D	D	D	D	D
0.12μF (124)	B	B	B	B	D		C	C	C	C	C	D	D	D	D	D	D
0.15μF (154)	C	C	C	C	G		C	C	C	C	C	D	D	D	D	D	D
0.18μF (184)	C	C	C	C	G		C	C	C	C	C	D	D	D	D	D	D
0.22μF (224)	C	C	C	C	G		C	C	C	C	C	D	D	D	D	D	D
0.27μF (274)	C	C	C	D	G		C	C	C	C	G	D	D	D	D	D	D
0.33μF (334)	C	C	C	D	G		C	C	C	D	G	D	D	D	D	D	D
0.39μF (394)	C	C	J	P	G		C	C	C	D	M	D	D	D	D	D	D
0.47μF (474)	J	J	J	P	G		C	C	C	D	M	D	D	D	D	D	K
0.56μF (564)	J	J	J	P	P		D	D	D	D	M	D	D	D	D	D	K
0.68μF (684)	J	J	J	P	P		D	D	D	D	K	D	D	D	K	K	K
0.82μF (824)	J	J	J	P	P		D	D	D	D	K	D	D	D	K	K	K
1.0μF (105)	J	J	J	P	P		D	D	D	D	K	D	D	D	K	K	K
1.5μF (155)	J	J	J	P			K	G	M	M							K
2.2μF (225)	J	J	J	P	P		K	G	M	M					M	M	
3.3μF (335)	P	P	P	P			K	G									
4.7μF (475)	P	P	P	P	P		K	K	K	M							
6.8μF (685)																	
10μF (106)	P	P	P	P			K	K	K	M							
22μF (226)	P	P	P*				M	M	M								
47μF (476)							M	M									
100μF (107)																	

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “*” mark is expressed product not in 10% (code “K”) tolerance.

7-3. Y5V Dielectric 0402, 0603, 0805 Sizes

DIELECTRIC		Y5V															
SIZE		0402					0603					0805					
RATED VOLTAGE (VDC)		6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50	100
Capacitance	0.010μF (103)	N	N	N	N		S	S	S	S		A	A	A	A	B	
	0.015μF (153)	N	N	N	N		S	S	S	S		A	A	A	A	B	
	0.022μF (223)	N	N	N	N		S	S	S	S		A	A	A	A	B	
	0.033μF (333)	N	N	N	N		S	S	S	S		A	A	A	A	B	
	0.047μF (473)	N	N	N			S	S	S	S		A	A	A	A	B	
	0.068μF (683)	N	N	N			S	S	S	S		A	A	A	A	B	
	0.10μF (104)	N	N	N			S	S	S	S		A	A	A	A	B	
	0.15μF (154)	N	N				S	S	S	S		A	A	A	A		
	0.22μF (224)	N	N	N			S	S	S	S		A	A	A	A		
	0.33μF (334)	N	N	N			S	S	S	X		B	B	B	B		
	0.47μF (474)	N	N	N			S	S	X	X		B	B	B	B		
	0.68μF (684)	N					S	X	X			B	B	D	D		
	1.0μF (105)	N	N				S	X	X			B	B	D	D		
	1.5μF (155)						S					D	D				
	2.2μF (225)						S	S	X			D	D	I			
	3.3μF (335)											D	D				
	4.7μF (475)						X	X				D	D	I			
	6.8μF (685)											I					
	10μF (106)											I	I	I			
	22μF (226)											I	I				

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

7-3. Y5V Dielectric 1206, 1210, 1812 Sizes

DIELECTRIC		Y5V																	
SIZE		1206					1210					1812							
RATED VOLTAGE (VDC)		6.3	10	16	25	50	100	6.3	10	16	25	35	50	100	10	16	25	50	100
Capacitance	0.010μF (103)	B	B	B	B	B						C					D		
	0.015μF (153)	B	B	B	B	B						C					D		
	0.022μF (223)	B	B	B	B	B						C					D		
	0.033μF (333)	B	B	B	B	B						C					D		
	0.047μF (473)	B	B	B	B	B						C					D		
	0.068μF (683)	B	B	B	B	B						C					D		
	0.10μF (104)	B	B	B	B	B		C	C	C		C	C	D	D	D	D		
	0.15μF (154)	B	B	B	B	C		C	C	C		C	C	D	D	D	D		
	0.22μF (224)	B	B	B	B	C		C	C	C		C	C	D	D	D	D		
	0.33μF (334)	B	B	B	B		C	C	C		C	C	D	D	D	D			
	0.47μF (474)	B	B	B	B		C	C	C		C		D	D	D	D			
	0.68μF (684)	B	B	B	B		C	C	C		C		D	D	D	D			
	1.0μF (105)	C	C	C	C		C	C	C		C		D	D	D	D			
	1.5μF (155)	C	C	C			C	C	C				D	D	D	D			
	2.2μF (225)	C	C	C	J		C	C	C		G		D	D	D	D			
	3.3μF (335)	J	J	J			C	C	C				D	D	D	D			
	4.7μF (475)	J	J	J	P		C	C	D		G		D	D	D	D			
	6.8μF (685)	J	J				C	C	D		K		D	D	D	D			
	10μF (106)	J	J	P			D	D	G	K	K		D	D	D	K			
	22μF (226)	P	P				K	K					M						
	47μF (476)	P					K	K											
	100μF (107)						M												

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

7-4. X5R Dielectric 0201, 0402, 0603, 0805, 1206, 1210 Sizes

Dielectric		X5R														
Size		0201					0402					0603				
Rated Voltage (VDC)	6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50	
Capacitance	100pF (101)		L	L	L											
	120pF (121)		L	L	L											
	150pF (151)		L	L	L											
	180pF (181)		L	L	L											
	220pF (221)		L	L	L											
	270pF (271)		L	L	L											
	330pF (331)		L	L	L											
	390pF (391)		L	L	L											
	470pF (471)		L	L	L											
	560pF (561)		L	L	L											
	680pF (681)		L	L	L											
	820pF (821)		L	L	L											
	1,000pF (102)	L	L	L	L											
	1,500pF (152)	L	L													
	2,200pF (222)	L	L													
	2,700pF (272)	L	L													
	3,300pF (332)	L	L													
	4,700pF (472)	L	L													
	6,800pF (682)	L														
	0.010μF (103)	L	L	L	L											
	0.015μF (153)	L	L													
	0.022μF (223)	L	L													
	0.027μF (273)	L	L					N								
	0.033μF (333)	L	L					N								
	0.039μF (393)	L	L					N								
	0.047μF (473)	L	L					N								
	0.056μF (563)	L	L					N	N							
	0.068μF (683)	L	L					N	N							
	0.082μF (823)	L	L			N		N	N							
	0.10μF (104)	L	L	L	L	N	N	N	N	N						
	0.15μF (154)					N	N	N	N	N						
	0.22μF (224)	L	L			N	N	N	N	N			X	X		
	0.27μF (274)											X	X	X		
	0.33μF (334)					N	N				X	X	X	X		
	0.39μF (394)										X	X	X	X		
	0.47μF (474)	L				N	N	E	E	E	X	X	X	X	X	
	0.68μF (684)					N	N				X	X	X	X		
	0.82μF (824)										X	X	X			
	1.0μF (105)	L	L*			N	N	N	N		X	X	X	X	X	
	1.5μF (155)										X					
	2.2μF (225)	L*				N	N	E	E		X	X	X	X	X	
	3.3μF (335)										X	X				
	4.7μF (475)					E*	E*	E*			X	X	X	X		
	6.8μF (685)															
	10μF (106)					E*	E*				X	X	X	X*		
	22μF (226)										X*	X*				

Dielectric		X5R															
Size		0805					1206					1210					
Rated Voltage (VDC)	4	6.3	10	16	25	50	6.3	10	16	25	50	4	6.3	10	16	25	50
Capacitance	1.0μF (105)		D	D	D	I											
	1.5μF (155)	I	I	I	I	I		J	J				K	K			
	2.2μF (225)	I	I	I	I	I		J	J	P	P		K	K			
	3.3μF (335)	I	I	I	I	I		P	P	P	P						
	4.7μF (475)	I	I	I	I	I	P	P	P	P	P		K	K	K		
	6.8μF (685)						P	P									
	10μF (106)	I	I	I	I	I	P	P	P	P	P		K	K	K	K	M
	22μF (226)	I	I*	I*	I*		P	P	P	P			M	M	M	M	
	47μF (476)	I*	I*				P	P					M	M	M	M	
	100μF (107)	I*					P*						M*	M*			
	220μF (227)											M*					

- The letter in cell is expressed the symbol of product thickness.
- The letter in cell with “*” mark is expressed product not in 10% (code “K”) tolerance.

7-5. X6S Dielectric 0201, 0402, 0603, 0805, 1206, 1210 Sizes

Dielectric		X6S																										
Size		0201				0402				0603				0805				1206				1210						
Rated Voltage (VDC)		4	6.3	6.3	10	16	25	4	6.3	10	16	25	4	6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50
Capacitance	0.10μF (104)	L	L																									
	0.15μF (154)																											
	0.22μF (224)		L																									
	0.33μF (334)																											
	0.47μF (474)		N																									
	0.68μF (684)																											
	1.0μF (105)	L*	N	E	E	E																						
	1.5μF (155)																											
	2.2μF (225)	N	E	E										X														
	3.3μF (335)																											
	4.7μF (475)									X	X	X					I	I										
	6.8uF (685)																											
	10μF (106)								X*	X*	X*			I	I	I	I	I				G						
	22μF (226)							X*	X*					I*	I*	I*			P	P*				M				
	47μF (476)													I*					P				M	M	M			
	100μF (107)																							M*				

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “*” mark is expressed product not in 10% (code “K”) tolerance.

8. PACKAGING STYLE AND QUANTITY

Size	Thickness (mm)/Symbol	Paper tape				Plastic tape			
		7" reel	13" reel	7" reel	13" reel				
0201 (0603)	0.30±0.03	L	15,000	70,000		-			-
	0.30±0.05	L	15,000	-		-			-
	0.30±0.09	L	15,000	-		-			-
0402 (1005)	0.50±0.05	N	10,000	50,000		-			-
	0.50+0.02/-0.05	Q	10,000	50,000		-			-
	0.50±0.20	E	10,000	-		-			-
0603 (1608)	0.50±0.10	H	4,000	-		-			-
	0.80±0.07	S	4,000	15,000		-			-
	0.80+0.15/-0.10	X	4,000	15,000		-			-
0805 (2012)	0.50±0.10	H	4,000	15,000		-			-
	0.60±0.10	A	4,000	15,000		-			-
	0.80±0.10	B	4,000	15,000		-			-
	0.85±0.10	T	4,000	15,000		-			-
	1.25±0.10	D	-	-		3,000		10,000	
	1.25±0.20	I	-	-		3,000		10,000	
1206 (3216)	0.80±0.10	B	4,000	15,000		-			-
	0.85±0.10	T	4,000	15,000		-			-
	0.95±0.10	C	-	-		3,000		10,000	
	1.15±0.15	J	-	-		3,000		10,000	
	1.25±0.10	D	-	-		3,000		10,000	
	1.60±0.20	G	-	-		2,000		10,000	
1210 (3225)	1.60+0.30/-0.10	P	-	-		2,000		9,000	
	0.85±0.10	T	-	-		3,000		10,000	
	0.95±0.10	C	-	-		3,000		10,000	
	1.25±0.10	D	-	-		3,000		10,000	
	1.60±0.20	G	-	-		2,000		-	
	2.00±0.20	K	-	-		1,000		6,000	
1808 (4520)	2.50±0.30	M	-	-		1,000		6,000	
	1.25±0.10	D	-	-		2,000		10,000	
	1.10±0.15	F	-	-		2,000		10,000	
	1.60±0.20	G	-	-		2,000		8,000	
1812 (4532)	2.00±0.20	K	-	-		1,000		6,000	
	1.25±0.10	D	-	-		1,000		5,000	
	1.60±0.20	G	-	-		1,000		-	
	2.00±0.20	K	-	-		1,000		-	
	2.50±0.30	M	-	-		500		3,000	
	2.80±0.30	U	-	-		500		-	

Unit: pieces

9. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																																																																																																																									
1.	Visual and Mechanical	---	* No remarkable defect. * Dimensions to conform to individual specification sheet.																																																																																																																									
2.	Capacitance	Class I: (NPO)	* Shall not exceed the limits given in the detailed spec.																																																																																																																									
3.	Q/D.F. (Dissipation Factor)	≤1000pF, 1.0±0.2Vrms · 1MHz±10% >1000pF, 1.0±0.2Vrms · 1KHz±10% Class II: (X7R, X7E, X6S, X5R, Y5V) C≤10μF, 1.0±0.2Vrms · 1KHz±10% ** C>10μF, 0.5±0.2Vrms · 120Hz±20%	NPO: Cap≥30pF, Q≥1000; Cap<30pF, Q≥400+20C X7R, X5R, X6S: <table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F.≤</th> <th>Exception of D.F.≤</th> </tr> </thead> <tbody> <tr> <td rowspan="2">≥100V</td> <td rowspan="2">≤2.5%</td> <td>≤3% 1206≥0.47μF</td> </tr> <tr> <td>≤5% 0805>0.1μF, 0603≥0.068μF, 1206>1μF; TT series</td> </tr> <tr> <td rowspan="4">50V</td> <td rowspan="4">≤2.5%</td> <td>≤3% 0201(50V); 0603≥0.047μF; 0805≥0.18μF; 1206≥0.47μF</td> </tr> <tr> <td>≤5% 1210≥4.7μF</td> </tr> <tr> <td>≤10% 0402≥0.1μF; 0603>0.1μF; 0805≥1μF; 1206≥2.2μF; 1210≥10μF; TT series</td> </tr> <tr> <td>≤12.5% 0402≥1μF</td> </tr> <tr> <td rowspan="4">35V</td> <td rowspan="4">≤3.5%</td> <td>≤10% 0603≥1μF; 0805≥2.2μF; 1210≥10μF</td> </tr> <tr> <td>≤5% 0201≥0.01μF; 0805≥1μF; 1210≥10μF</td> </tr> <tr> <td>≤7% 0603≥0.33μF; 1206≥4.7μF</td> </tr> <tr> <td>≤10% 0402≥0.10μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥6.8μF; 1210≥22μF; TT series</td> </tr> <tr> <td rowspan="4">25V</td> <td rowspan="4">≤3.5%</td> <td>≤12.5% 0402≥1μF</td> </tr> <tr> <td>≤5% 0201≥0.01μF; 0402≥0.033μF; 0603≥0.15μF; 0805≥0.68μF; 1206≥2.2μF; 1210≥4.7μF</td> </tr> <tr> <td>≤10% 0201≥0.1uF; 0402≥0.22uF; 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series</td> </tr> <tr> <td>≤15% 0201≥0.1μF; 0402≥1μF</td> </tr> <tr> <td rowspan="4">16V</td> <td rowspan="4">≤3.5%</td> <td>≤10% 0201≥0.012μF; 0402≥0.33μF (0402/X7R≥0.22μF); TT series</td> </tr> <tr> <td>≤15% 0603≥0.33μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥22μF</td> </tr> <tr> <td>≤20% 0201≥0.1μF; 0402≥1μF</td> </tr> <tr> <td>≤25% 0201≥0.15μF; 0402≥1.5μF; 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF; TT series</td> </tr> <tr> <td rowspan="4">10V</td> <td rowspan="4">≤5%</td> <td>≤10% 0201≥0.1μF; 0402≥1μF; 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series</td> </tr> <tr> <td>≤15% 0201≥0.15μF; 0402≥1.5μF</td> </tr> <tr> <td>≤20% 0201≥0.2μF</td> </tr> <tr> <td>≤25% 0201≥0.25μF</td> </tr> <tr> <td rowspan="4">6.3V</td> <td rowspan="4">≤10%</td> <td>≤15% 0201≥0.1μF; 0402≥1μF; 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series</td> </tr> <tr> <td>≤20% 0402≥2.2μF</td> </tr> <tr> <td>≤25% 0402≥4.7μF</td> </tr> <tr> <td>≤30% 0402≥7μF</td> </tr> <tr> <td rowspan="4">4V</td> <td rowspan="4">≤15%</td> <td>≤15% ---</td> </tr> <tr> <td>≤20% ---</td> </tr> <tr> <td>≤25% ---</td> </tr> <tr> <td>≤30% ---</td> </tr> <tr> <td colspan="6" style="text-align: center;">Y5V:</td></tr> <tr> <td colspan="5" style="text-align: center;"> <table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F.≤</th> <th>Exception of D.F.≤</th> </tr> </thead> <tbody> <tr> <td>≥50V</td> <td>5%</td> <td>7% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF</td> </tr> <tr> <td>35V</td> <td>7%</td> <td>---</td> </tr> <tr> <td>25V</td> <td>5%</td> <td>7% 0402≥0.047μF; 0603≥0.1μF; 9% 0805≥0.33μF; 1206≥1μF; 1210≥4.7μF</td> </tr> <tr> <td>16V (C<1.0μF)</td> <td>7%</td> <td>9% 0402≥0.068μF; 0603≥0.47μF; 1206≥4.7μF; 1210≥22μF</td> </tr> <tr> <td>16V (C≥1.0μF)</td> <td>9%</td> <td>12.5% 0402≥0.22μF</td> </tr> <tr> <td>10V</td> <td>12.5%</td> <td>20% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF</td> </tr> <tr> <td>6.3V</td> <td>20%</td> <td>---</td> </tr> </tbody> </table> </td></tr> <tr> <td>4.</td><td>Dielectric Strength</td><td> * To apply voltage (≤100V) 250%. * Duration: 1 to 5 sec. * Charge and discharge current less than 50mA. </td><td colspan="3"> * No evidence of damage or flash over during test. </td></tr> <tr> <td>5.</td><td>Insulation Resistance</td><td> To apply rated voltage for max. 120 sec. </td><td colspan="3"> 10GΩ or Rx_C≥500Ω-F whichever is smaller. Class II (X7R, X5R, X6S, Y5V) </td></tr> <tr> <td></td><td></td><td></td><td> <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: X7R</td> <td rowspan="7">10GΩ or Rx_C≥100Ω-F whichever is smaller.</td> </tr> <tr> <td>50V: 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF</td> </tr> <tr> <td>35V: 0805≥2.2μF; 1210≥10μF</td> </tr> <tr> <td>25V: 0402≥1μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF</td> </tr> <tr> <td>16V: 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF</td> </tr> <tr> <td>10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF</td> </tr> <tr> <td>6.3V ; 4V</td> </tr> </tbody> </table> <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>All X6S items</td> <td rowspan="7">Rx_C≥50Ω-F.</td> </tr> <tr> <td>50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF; 1206≥10μF</td> </tr> <tr> <td>35V: 0603≥1μF;</td> </tr> <tr> <td>25V: 0201≥0.1μF; 0402≥0.22μF; 0603≥10μF; 0805≥10μF; 1206≥22μF</td> </tr> <tr> <td>16V: 0603≥10μF</td> </tr> <tr> <td>10V: 0201≥0.1μF; 0603≥10μF; 0805≥47μF</td> </tr> <tr> <td>6.3V: 0201≥0.1μF; 1206≥10μF</td> </tr> <tr> <td>4V: 0603≥22μF; 0805≥47μF</td> </tr> </tbody> </table> </td></tr> </tbody> </table>	Rated vol.	D.F.≤	Exception of D.F.≤	≥100V	≤2.5%	≤3% 1206≥0.47μF	≤5% 0805>0.1μF, 0603≥0.068μF, 1206>1μF; TT series	50V	≤2.5%	≤3% 0201(50V); 0603≥0.047μF; 0805≥0.18μF; 1206≥0.47μF	≤5% 1210≥4.7μF	≤10% 0402≥0.1μF; 0603>0.1μF; 0805≥1μF; 1206≥2.2μF; 1210≥10μF; TT series	≤12.5% 0402≥1μF	35V	≤3.5%	≤10% 0603≥1μF; 0805≥2.2μF; 1210≥10μF	≤5% 0201≥0.01μF; 0805≥1μF; 1210≥10μF	≤7% 0603≥0.33μF; 1206≥4.7μF	≤10% 0402≥0.10μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥6.8μF; 1210≥22μF; TT series	25V	≤3.5%	≤12.5% 0402≥1μF	≤5% 0201≥0.01μF; 0402≥0.033μF; 0603≥0.15μF; 0805≥0.68μF; 1206≥2.2μF; 1210≥4.7μF	≤10% 0201≥0.1uF; 0402≥0.22uF; 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series	≤15% 0201≥0.1μF; 0402≥1μF	16V	≤3.5%	≤10% 0201≥0.012μF; 0402≥0.33μF (0402/X7R≥0.22μF); TT series	≤15% 0603≥0.33μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥22μF	≤20% 0201≥0.1μF; 0402≥1μF	≤25% 0201≥0.15μF; 0402≥1.5μF; 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF; TT series	10V	≤5%	≤10% 0201≥0.1μF; 0402≥1μF; 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series	≤15% 0201≥0.15μF; 0402≥1.5μF	≤20% 0201≥0.2μF	≤25% 0201≥0.25μF	6.3V	≤10%	≤15% 0201≥0.1μF; 0402≥1μF; 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series	≤20% 0402≥2.2μF	≤25% 0402≥4.7μF	≤30% 0402≥7μF	4V	≤15%	≤15% ---	≤20% ---	≤25% ---	≤30% ---	Y5V:						<table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F.≤</th> <th>Exception of D.F.≤</th> </tr> </thead> <tbody> <tr> <td>≥50V</td> <td>5%</td> <td>7% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF</td> </tr> <tr> <td>35V</td> <td>7%</td> <td>---</td> </tr> <tr> <td>25V</td> <td>5%</td> <td>7% 0402≥0.047μF; 0603≥0.1μF; 9% 0805≥0.33μF; 1206≥1μF; 1210≥4.7μF</td> </tr> <tr> <td>16V (C<1.0μF)</td> <td>7%</td> <td>9% 0402≥0.068μF; 0603≥0.47μF; 1206≥4.7μF; 1210≥22μF</td> </tr> <tr> <td>16V (C≥1.0μF)</td> <td>9%</td> <td>12.5% 0402≥0.22μF</td> </tr> <tr> <td>10V</td> <td>12.5%</td> <td>20% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF</td> </tr> <tr> <td>6.3V</td> <td>20%</td> <td>---</td> </tr> </tbody> </table>					Rated vol.	D.F.≤	Exception of D.F.≤	≥50V	5%	7% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF	35V	7%	---	25V	5%	7% 0402≥0.047μF; 0603≥0.1μF; 9% 0805≥0.33μF; 1206≥1μF; 1210≥4.7μF	16V (C<1.0μF)	7%	9% 0402≥0.068μF; 0603≥0.47μF; 1206≥4.7μF; 1210≥22μF	16V (C≥1.0μF)	9%	12.5% 0402≥0.22μF	10V	12.5%	20% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF	6.3V	20%	---	4.	Dielectric Strength	* To apply voltage (≤100V) 250%. * Duration: 1 to 5 sec. * Charge and discharge current less than 50mA.	* No evidence of damage or flash over during test.			5.	Insulation Resistance	To apply rated voltage for max. 120 sec.	10GΩ or Rx _C ≥500Ω-F whichever is smaller. Class II (X7R, X5R, X6S, Y5V)						<table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: X7R</td> <td rowspan="7">10GΩ or Rx_C≥100Ω-F whichever is smaller.</td> </tr> <tr> <td>50V: 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF</td> </tr> <tr> <td>35V: 0805≥2.2μF; 1210≥10μF</td> </tr> <tr> <td>25V: 0402≥1μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF</td> </tr> <tr> <td>16V: 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF</td> </tr> <tr> <td>10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF</td> </tr> <tr> <td>6.3V ; 4V</td> </tr> </tbody> </table> <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>All X6S items</td> <td rowspan="7">Rx_C≥50Ω-F.</td> </tr> <tr> <td>50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF; 1206≥10μF</td> </tr> <tr> <td>35V: 0603≥1μF;</td> </tr> <tr> <td>25V: 0201≥0.1μF; 0402≥0.22μF; 0603≥10μF; 0805≥10μF; 1206≥22μF</td> </tr> <tr> <td>16V: 0603≥10μF</td> </tr> <tr> <td>10V: 0201≥0.1μF; 0603≥10μF; 0805≥47μF</td> </tr> <tr> <td>6.3V: 0201≥0.1μF; 1206≥10μF</td> </tr> <tr> <td>4V: 0603≥22μF; 0805≥47μF</td> </tr> </tbody> </table>	Rated voltage	Insulation Resistance	100V: X7R	10GΩ or Rx _C ≥100Ω-F whichever is smaller.	50V: 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF	35V: 0805≥2.2μF; 1210≥10μF	25V: 0402≥1μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF	16V: 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF	10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF	6.3V ; 4V	Rated voltage	Insulation Resistance	All X6S items	Rx _C ≥50Ω-F.	50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF; 1206≥10μF	35V: 0603≥1μF;	25V: 0201≥0.1μF; 0402≥0.22μF; 0603≥10μF; 0805≥10μF; 1206≥22μF	16V: 0603≥10μF	10V: 0201≥0.1μF; 0603≥10μF; 0805≥47μF	6.3V: 0201≥0.1μF; 1206≥10μF	4V: 0603≥22μF; 0805≥47μF
Rated vol.	D.F.≤	Exception of D.F.≤																																																																																																																										
≥100V	≤2.5%	≤3% 1206≥0.47μF																																																																																																																										
		≤5% 0805>0.1μF, 0603≥0.068μF, 1206>1μF; TT series																																																																																																																										
50V	≤2.5%	≤3% 0201(50V); 0603≥0.047μF; 0805≥0.18μF; 1206≥0.47μF																																																																																																																										
		≤5% 1210≥4.7μF																																																																																																																										
		≤10% 0402≥0.1μF; 0603>0.1μF; 0805≥1μF; 1206≥2.2μF; 1210≥10μF; TT series																																																																																																																										
		≤12.5% 0402≥1μF																																																																																																																										
35V	≤3.5%	≤10% 0603≥1μF; 0805≥2.2μF; 1210≥10μF																																																																																																																										
		≤5% 0201≥0.01μF; 0805≥1μF; 1210≥10μF																																																																																																																										
		≤7% 0603≥0.33μF; 1206≥4.7μF																																																																																																																										
		≤10% 0402≥0.10μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥6.8μF; 1210≥22μF; TT series																																																																																																																										
25V	≤3.5%	≤12.5% 0402≥1μF																																																																																																																										
		≤5% 0201≥0.01μF; 0402≥0.033μF; 0603≥0.15μF; 0805≥0.68μF; 1206≥2.2μF; 1210≥4.7μF																																																																																																																										
		≤10% 0201≥0.1uF; 0402≥0.22uF; 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series																																																																																																																										
		≤15% 0201≥0.1μF; 0402≥1μF																																																																																																																										
16V	≤3.5%	≤10% 0201≥0.012μF; 0402≥0.33μF (0402/X7R≥0.22μF); TT series																																																																																																																										
		≤15% 0603≥0.33μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥22μF																																																																																																																										
		≤20% 0201≥0.1μF; 0402≥1μF																																																																																																																										
		≤25% 0201≥0.15μF; 0402≥1.5μF; 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF; TT series																																																																																																																										
10V	≤5%	≤10% 0201≥0.1μF; 0402≥1μF; 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series																																																																																																																										
		≤15% 0201≥0.15μF; 0402≥1.5μF																																																																																																																										
		≤20% 0201≥0.2μF																																																																																																																										
		≤25% 0201≥0.25μF																																																																																																																										
6.3V	≤10%	≤15% 0201≥0.1μF; 0402≥1μF; 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF; TT series																																																																																																																										
		≤20% 0402≥2.2μF																																																																																																																										
		≤25% 0402≥4.7μF																																																																																																																										
		≤30% 0402≥7μF																																																																																																																										
4V	≤15%	≤15% ---																																																																																																																										
		≤20% ---																																																																																																																										
		≤25% ---																																																																																																																										
		≤30% ---																																																																																																																										
Y5V:																																																																																																																												
<table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F.≤</th> <th>Exception of D.F.≤</th> </tr> </thead> <tbody> <tr> <td>≥50V</td> <td>5%</td> <td>7% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF</td> </tr> <tr> <td>35V</td> <td>7%</td> <td>---</td> </tr> <tr> <td>25V</td> <td>5%</td> <td>7% 0402≥0.047μF; 0603≥0.1μF; 9% 0805≥0.33μF; 1206≥1μF; 1210≥4.7μF</td> </tr> <tr> <td>16V (C<1.0μF)</td> <td>7%</td> <td>9% 0402≥0.068μF; 0603≥0.47μF; 1206≥4.7μF; 1210≥22μF</td> </tr> <tr> <td>16V (C≥1.0μF)</td> <td>9%</td> <td>12.5% 0402≥0.22μF</td> </tr> <tr> <td>10V</td> <td>12.5%</td> <td>20% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF</td> </tr> <tr> <td>6.3V</td> <td>20%</td> <td>---</td> </tr> </tbody> </table>					Rated vol.	D.F.≤	Exception of D.F.≤	≥50V	5%	7% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF	35V	7%	---	25V	5%	7% 0402≥0.047μF; 0603≥0.1μF; 9% 0805≥0.33μF; 1206≥1μF; 1210≥4.7μF	16V (C<1.0μF)	7%	9% 0402≥0.068μF; 0603≥0.47μF; 1206≥4.7μF; 1210≥22μF	16V (C≥1.0μF)	9%	12.5% 0402≥0.22μF	10V	12.5%	20% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF	6.3V	20%	---																																																																																																
Rated vol.	D.F.≤	Exception of D.F.≤																																																																																																																										
≥50V	5%	7% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF																																																																																																																										
35V	7%	---																																																																																																																										
25V	5%	7% 0402≥0.047μF; 0603≥0.1μF; 9% 0805≥0.33μF; 1206≥1μF; 1210≥4.7μF																																																																																																																										
16V (C<1.0μF)	7%	9% 0402≥0.068μF; 0603≥0.47μF; 1206≥4.7μF; 1210≥22μF																																																																																																																										
16V (C≥1.0μF)	9%	12.5% 0402≥0.22μF																																																																																																																										
10V	12.5%	20% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF																																																																																																																										
6.3V	20%	---																																																																																																																										
4.	Dielectric Strength	* To apply voltage (≤100V) 250%. * Duration: 1 to 5 sec. * Charge and discharge current less than 50mA.	* No evidence of damage or flash over during test.																																																																																																																									
5.	Insulation Resistance	To apply rated voltage for max. 120 sec.	10GΩ or Rx _C ≥500Ω-F whichever is smaller. Class II (X7R, X5R, X6S, Y5V)																																																																																																																									
			<table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: X7R</td> <td rowspan="7">10GΩ or Rx_C≥100Ω-F whichever is smaller.</td> </tr> <tr> <td>50V: 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF</td> </tr> <tr> <td>35V: 0805≥2.2μF; 1210≥10μF</td> </tr> <tr> <td>25V: 0402≥1μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF</td> </tr> <tr> <td>16V: 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF</td> </tr> <tr> <td>10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF</td> </tr> <tr> <td>6.3V ; 4V</td> </tr> </tbody> </table> <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>All X6S items</td> <td rowspan="7">Rx_C≥50Ω-F.</td> </tr> <tr> <td>50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF; 1206≥10μF</td> </tr> <tr> <td>35V: 0603≥1μF;</td> </tr> <tr> <td>25V: 0201≥0.1μF; 0402≥0.22μF; 0603≥10μF; 0805≥10μF; 1206≥22μF</td> </tr> <tr> <td>16V: 0603≥10μF</td> </tr> <tr> <td>10V: 0201≥0.1μF; 0603≥10μF; 0805≥47μF</td> </tr> <tr> <td>6.3V: 0201≥0.1μF; 1206≥10μF</td> </tr> <tr> <td>4V: 0603≥22μF; 0805≥47μF</td> </tr> </tbody> </table>	Rated voltage	Insulation Resistance	100V: X7R	10GΩ or Rx _C ≥100Ω-F whichever is smaller.	50V: 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF	35V: 0805≥2.2μF; 1210≥10μF	25V: 0402≥1μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF	16V: 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF	10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF	6.3V ; 4V	Rated voltage	Insulation Resistance	All X6S items	Rx _C ≥50Ω-F.	50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF; 1206≥10μF	35V: 0603≥1μF;	25V: 0201≥0.1μF; 0402≥0.22μF; 0603≥10μF; 0805≥10μF; 1206≥22μF	16V: 0603≥10μF	10V: 0201≥0.1μF; 0603≥10μF; 0805≥47μF	6.3V: 0201≥0.1μF; 1206≥10μF	4V: 0603≥22μF; 0805≥47μF																																																																																																				
Rated voltage	Insulation Resistance																																																																																																																											
100V: X7R	10GΩ or Rx _C ≥100Ω-F whichever is smaller.																																																																																																																											
50V: 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF																																																																																																																												
35V: 0805≥2.2μF; 1210≥10μF																																																																																																																												
25V: 0402≥1μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF																																																																																																																												
16V: 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF																																																																																																																												
10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF																																																																																																																												
6.3V ; 4V																																																																																																																												
Rated voltage	Insulation Resistance																																																																																																																											
All X6S items	Rx _C ≥50Ω-F.																																																																																																																											
50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF; 1206≥10μF																																																																																																																												
35V: 0603≥1μF;																																																																																																																												
25V: 0201≥0.1μF; 0402≥0.22μF; 0603≥10μF; 0805≥10μF; 1206≥22μF																																																																																																																												
16V: 0603≥10μF																																																																																																																												
10V: 0201≥0.1μF; 0603≥10μF; 0805≥47μF																																																																																																																												
6.3V: 0201≥0.1μF; 1206≥10μF																																																																																																																												
4V: 0603≥22μF; 0805≥47μF																																																																																																																												

No.	Item	Test Condition	Requirements																								
6.	Temperature Coefficient	With no electrical load. <table border="1"> <thead> <tr> <th>T.C.</th> <th>Operating Temp</th> </tr> </thead> <tbody> <tr> <td>NPO</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X7R</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X5R</td> <td>-55~ 85°C at 25°C</td> </tr> <tr> <td>X6S</td> <td>-55~105°C at 25°C</td> </tr> <tr> <td>Y5V</td> <td>-25~ 85°C at 20°C</td> </tr> </tbody> </table>	T.C.	Operating Temp	NPO	-55~125°C at 25°C	X7R	-55~125°C at 25°C	X5R	-55~ 85°C at 25°C	X6S	-55~105°C at 25°C	Y5V	-25~ 85°C at 20°C	<table border="1"> <thead> <tr> <th>T.C.</th> <th>Capacitance Change</th> </tr> </thead> <tbody> <tr> <td>NPO</td> <td>Within ±30ppm/°C</td> </tr> <tr> <td>X7R</td> <td>Within ±15%</td> </tr> <tr> <td>X5R</td> <td>Within ±15%</td> </tr> <tr> <td>X6S</td> <td>Within ±22%</td> </tr> <tr> <td>Y5V</td> <td>Within +30%/-80%</td> </tr> </tbody> </table>	T.C.	Capacitance Change	NPO	Within ±30ppm/°C	X7R	Within ±15%	X5R	Within ±15%	X6S	Within ±22%	Y5V	Within +30%/-80%
T.C.	Operating Temp																										
NPO	-55~125°C at 25°C																										
X7R	-55~125°C at 25°C																										
X5R	-55~ 85°C at 25°C																										
X6S	-55~105°C at 25°C																										
Y5V	-25~ 85°C at 20°C																										
T.C.	Capacitance Change																										
NPO	Within ±30ppm/°C																										
X7R	Within ±15%																										
X5R	Within ±15%																										
X6S	Within ±22%																										
Y5V	Within +30%/-80%																										
7.	Adhesive Strength of Termination	* Pressurizing force : 1N (0201) and 5N (≤0603) and 10N (>0603) * Test time: 10±1 sec.	* No remarkable damage or removal of the terminations.																								
8.	Vibration Resistance	* Vibration frequency: 10~55 Hz/min. * Total amplitude: 1.5mm * Test time: 6 hrs. (Two hrs each in three mutually perpendicular directions.) * Measurement to be made after keeping at room temp. for 24±2 hrs.	* No remarkable damage. * Cap change and Q/D.F.: To meet initial spec.																								
9.	Solderability	* Solder temperature: 235±5°C * Dipping time: 2±0.5 sec.	95% min. coverage of all metallized area.																								
10.	Bending Test	* The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5±1 sec. * Measurement to be made after keeping at room temp. for 24±2 hrs.	* No remarkable damage. * Cap change : NP0: within ±5% or 0.5pF whichever is larger X7R, X5R, X6S: within ±12.5% Y5V: within ±30% (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.)																								
11.	Resistance to Soldering Heat	* Solder temperature: 260±5°C * Dipping time: 10±1 sec * Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs.	* No remarkable damage. * Cap change: NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R, X6S: within ±7.5% Y5V: within ±20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements. * 25% max. leaching on each edge.																								
12.	Temperature Cycle	* Conduct the five cycles according to the temperatures and time. <table border="1"> <thead> <tr> <th>Step</th> <th>Temp. (°C)</th> <th>Time (min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating temp. +0/-3</td> <td>30±3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30±3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table> * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs.	Step	Temp. (°C)	Time (min.)	1	Min. operating temp. +0/-3	30±3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2~3	* No remarkable damage. Cap change : NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R, X6S: within ±7.5% Y5V: within ±20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements.									
Step	Temp. (°C)	Time (min.)																									
1	Min. operating temp. +0/-3	30±3																									
2	Room temp.	2~3																									
3	Max. operating temp. +3/-0	30±3																									
4	Room temp.	2~3																									




No.	Item	Test Condition	Requirements																																																			
13.	Humidity (Damp Heat) Steady State	<ul style="list-style-type: none"> * Test temp.: $40 \pm 2^\circ\text{C}$ * Humidity: 90~95% RH * Test time: $500+24/-0\text{hrs}$. * Before initial measurement (Class II only): Perform $150+0/-10^\circ\text{C}$ for 1 hr and then set for 24 ± 2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24 ± 2 hrs. 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change: XPO: within $\pm 5\%$ or $0.5\mu\text{F}$ whichever is larger X7R, X5R, X6S: $\geq 10\text{V}^{**}$, within $\pm 12.5\%$; $\leq 6.3\text{V}$ within $\pm 25\%$; TT series & $C \geq 1\mu\text{F}$, within $\pm 25\%$ $**10\text{V}$: 0603 $\geq 4.7\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; 0201 $\geq 0.1\mu\text{F}$, within $\pm 25\%$ $Y5V$: $\geq 10\text{V}$, within $\pm 30\%$; $\leq 6.3\text{V}$, within $+30/-40\%$ * Q.D.F. value: NPO: More than 30pF $Q \geq 350$, $10\text{pF} \leq C \leq 30\text{pF}$, $Q \geq 275+2.5\text{C}$ Less than 10pF $Q \geq 200+10\text{C}$ <p>X7R, X5R, X6S:</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Rated vol.</th> <th>D.F. \leq</th> <th>Exception of D.F. \leq</th> </tr> </thead> <tbody> <tr> <td>$\geq 100\text{V}$</td> <td>$\leq 3\%$</td> <td>$\leq 6\%$ 1206 $\geq 0.47\mu\text{F}$ $\leq 7.5\%$ 0805 $\geq 0.1\mu\text{F}$; 0603 $\geq 0.068\mu\text{F}$; 1206 $> 1\mu\text{F}$; TT series</td> </tr> <tr> <td>$\geq 50\text{V}$</td> <td>$\leq 3\%$</td> <td>$\leq 6\%$ 0201(50V); 0603 $\geq 0.047\mu\text{F}$; 0805 $\geq 0.18\mu\text{F}$; 1206 $\geq 0.47\mu\text{F}$ $\leq 10\%$ 1210 $\geq 4.7\mu\text{F}$ $\leq 20\%$ 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$; TT series</td> </tr> <tr> <td>35V</td> <td>$\leq 5\%$</td> <td>$\leq 20\%$ 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$ $\leq 10\%$ 0201 $\geq 0.01\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1210 $\geq 10\mu\text{F}$ $\leq 14\%$ 0603 $\geq 0.33\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$ $\leq 15\%$ 0402 $\geq 0.10\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 6.8\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; TT series $\leq 20\%$ 0402 $\geq 1\mu\text{F}$</td> </tr> <tr> <td>25V</td> <td>$\leq 5\%$</td> <td>$\leq 10\%$ 0603 $\geq 0.15\mu\text{F}$; 0805 $\geq 0.68\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$ $\leq 15\%$ 0201 $\geq 0.01\mu\text{F}$; 0402 $\geq 0.033\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; TT series</td> </tr> <tr> <td>16V</td> <td>$\leq 5\%$</td> <td>$\leq 15\%$ 0201 $\geq 0.012\mu\text{F}$; 0402 $\geq 0.33\mu\text{F}$ (0402/X7R $\geq 0.22\mu\text{F}$); 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$ $\leq 20\%$ 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; TT series</td> </tr> <tr> <td>10V</td> <td>$\leq 7.5\%$</td> <td>$\leq 15\%$ 0201 $\geq 0.012\mu\text{F}$; 0402 $\geq 0.33\mu\text{F}$ (0402/X7R $\geq 0.22\mu\text{F}$); 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$ $\leq 20\%$ 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; TT series</td> </tr> <tr> <td>6.3V</td> <td>$\leq 15\%$</td> <td>$\leq 30\%$ 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$; TT series</td> </tr> <tr> <td>4V</td> <td>$\leq 20\%$</td> <td>---</td> </tr> </tbody> </table> <p>Y5V:</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Rated vol.</th> <th>D.F. \leq</th> <th>Exception of D.F. \leq</th> </tr> </thead> <tbody> <tr> <td>$\geq 50\text{V}$</td> <td>7.5%</td> <td>10% 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$</td> </tr> <tr> <td>35V</td> <td>10%</td> <td>---</td> </tr> <tr> <td>25V</td> <td>7.5%</td> <td>10% 0402 $\geq 0.047\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.33\mu\text{F}$; 1206 $\geq 1\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$ 15% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$</td> </tr> <tr> <td>16V ($C < 1.0\mu\text{F}$)</td> <td>10%</td> <td>12.5% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$ 20% 0402 $\geq 0.22\mu\text{F}$</td> </tr> <tr> <td>16V ($C \geq 1.0\mu\text{F}$)</td> <td>12.5%</td> <td>20% 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 3.3\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; 1812 $\geq 47\mu\text{F}$</td> </tr> <tr> <td>10V</td> <td>20%</td> <td>30% 0402 $\geq 0.47\mu\text{F}$</td> </tr> <tr> <td>6.3V</td> <td>30%</td> <td>---</td> </tr> </tbody> </table>	Rated vol.	D.F. \leq	Exception of D.F. \leq	$\geq 100\text{V}$	$\leq 3\%$	$\leq 6\%$ 1206 $\geq 0.47\mu\text{F}$ $\leq 7.5\%$ 0805 $\geq 0.1\mu\text{F}$; 0603 $\geq 0.068\mu\text{F}$; 1206 $> 1\mu\text{F}$; TT series	$\geq 50\text{V}$	$\leq 3\%$	$\leq 6\%$ 0201(50V); 0603 $\geq 0.047\mu\text{F}$; 0805 $\geq 0.18\mu\text{F}$; 1206 $\geq 0.47\mu\text{F}$ $\leq 10\%$ 1210 $\geq 4.7\mu\text{F}$ $\leq 20\%$ 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$; TT series	35V	$\leq 5\%$	$\leq 20\%$ 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$ $\leq 10\%$ 0201 $\geq 0.01\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1210 $\geq 10\mu\text{F}$ $\leq 14\%$ 0603 $\geq 0.33\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$ $\leq 15\%$ 0402 $\geq 0.10\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 6.8\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; TT series $\leq 20\%$ 0402 $\geq 1\mu\text{F}$	25V	$\leq 5\%$	$\leq 10\%$ 0603 $\geq 0.15\mu\text{F}$; 0805 $\geq 0.68\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$ $\leq 15\%$ 0201 $\geq 0.01\mu\text{F}$; 0402 $\geq 0.033\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; TT series	16V	$\leq 5\%$	$\leq 15\%$ 0201 $\geq 0.012\mu\text{F}$; 0402 $\geq 0.33\mu\text{F}$ (0402/X7R $\geq 0.22\mu\text{F}$); 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$ $\leq 20\%$ 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; TT series	10V	$\leq 7.5\%$	$\leq 15\%$ 0201 $\geq 0.012\mu\text{F}$; 0402 $\geq 0.33\mu\text{F}$ (0402/X7R $\geq 0.22\mu\text{F}$); 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$ $\leq 20\%$ 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; TT series	6.3V	$\leq 15\%$	$\leq 30\%$ 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$; TT series	4V	$\leq 20\%$	---	Rated vol.	D.F. \leq	Exception of D.F. \leq	$\geq 50\text{V}$	7.5%	10% 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$	35V	10%	---	25V	7.5%	10% 0402 $\geq 0.047\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.33\mu\text{F}$; 1206 $\geq 1\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$ 15% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$	16V ($C < 1.0\mu\text{F}$)	10%	12.5% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$ 20% 0402 $\geq 0.22\mu\text{F}$	16V ($C \geq 1.0\mu\text{F}$)	12.5%	20% 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 3.3\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; 1812 $\geq 47\mu\text{F}$	10V	20%	30% 0402 $\geq 0.47\mu\text{F}$	6.3V	30%	---
Rated vol.	D.F. \leq	Exception of D.F. \leq																																																				
$\geq 100\text{V}$	$\leq 3\%$	$\leq 6\%$ 1206 $\geq 0.47\mu\text{F}$ $\leq 7.5\%$ 0805 $\geq 0.1\mu\text{F}$; 0603 $\geq 0.068\mu\text{F}$; 1206 $> 1\mu\text{F}$; TT series																																																				
$\geq 50\text{V}$	$\leq 3\%$	$\leq 6\%$ 0201(50V); 0603 $\geq 0.047\mu\text{F}$; 0805 $\geq 0.18\mu\text{F}$; 1206 $\geq 0.47\mu\text{F}$ $\leq 10\%$ 1210 $\geq 4.7\mu\text{F}$ $\leq 20\%$ 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$; TT series																																																				
35V	$\leq 5\%$	$\leq 20\%$ 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$ $\leq 10\%$ 0201 $\geq 0.01\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1210 $\geq 10\mu\text{F}$ $\leq 14\%$ 0603 $\geq 0.33\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$ $\leq 15\%$ 0402 $\geq 0.10\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 6.8\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; TT series $\leq 20\%$ 0402 $\geq 1\mu\text{F}$																																																				
25V	$\leq 5\%$	$\leq 10\%$ 0603 $\geq 0.15\mu\text{F}$; 0805 $\geq 0.68\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$ $\leq 15\%$ 0201 $\geq 0.01\mu\text{F}$; 0402 $\geq 0.033\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; TT series																																																				
16V	$\leq 5\%$	$\leq 15\%$ 0201 $\geq 0.012\mu\text{F}$; 0402 $\geq 0.33\mu\text{F}$ (0402/X7R $\geq 0.22\mu\text{F}$); 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$ $\leq 20\%$ 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; TT series																																																				
10V	$\leq 7.5\%$	$\leq 15\%$ 0201 $\geq 0.012\mu\text{F}$; 0402 $\geq 0.33\mu\text{F}$ (0402/X7R $\geq 0.22\mu\text{F}$); 0603 $\geq 0.33\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 2.2\mu\text{F}$; 1210 $\geq 22\mu\text{F}$ $\leq 20\%$ 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; TT series																																																				
6.3V	$\leq 15\%$	$\leq 30\%$ 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; 0603 $\geq 10\mu\text{F}$; 0805 $\geq 4.7\mu\text{F}$; 1206 $\geq 47\mu\text{F}$; 1210 $\geq 100\mu\text{F}$; TT series																																																				
4V	$\leq 20\%$	---																																																				
Rated vol.	D.F. \leq	Exception of D.F. \leq																																																				
$\geq 50\text{V}$	7.5%	10% 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$																																																				
35V	10%	---																																																				
25V	7.5%	10% 0402 $\geq 0.047\mu\text{F}$; 0603 $\geq 0.1\mu\text{F}$; 0805 $\geq 0.33\mu\text{F}$; 1206 $\geq 1\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$ 15% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 22\mu\text{F}$																																																				
16V ($C < 1.0\mu\text{F}$)	10%	12.5% 0402 $\geq 0.068\mu\text{F}$; 0603 $\geq 0.68\mu\text{F}$ 20% 0402 $\geq 0.22\mu\text{F}$																																																				
16V ($C \geq 1.0\mu\text{F}$)	12.5%	20% 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 3.3\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 22\mu\text{F}$; 1812 $\geq 47\mu\text{F}$																																																				
10V	20%	30% 0402 $\geq 0.47\mu\text{F}$																																																				
6.3V	30%	---																																																				

*I.R.: $\geq 10\text{V}$, $1\text{G}\Omega$ or $50\ \Omega\text{-F}$ whichever is smaller.

Class II (X7R, X5R, X6S, Y5V)



Rated voltage	Insulation Resistance
100V: X7R	
50V: 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$	
35V: 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$	
25V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 10\mu\text{F}$	1G Ω or $R_x C \geq 10\ \Omega\text{-F}$ whichever is smaller.
16V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 47\mu\text{F}$	
10V: 0201 $\geq 47\text{nF}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$	
6.3V ; 4V ; TT series ; All X6S items	

No	Item	Test Condition	Requirements			
14	Humidity (Damp Heat) Load	<ul style="list-style-type: none"> * Test temp.: $40 \pm 2^\circ\text{C}$ * Humidity: 90~95%RH * Test time: $500+24/-0$ hrs. * To apply voltage : rated voltage. * Before initial measurement (Class II only): To apply test voltage for 1hr at 40°C and then set for 24 ± 2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24 ± 2 hrs. 	<ul style="list-style-type: none"> * No remarkable damage. Cap change: NPO: $\pm 7.5\%$ or $0.75\mu\text{F}$ whichever is larger. X7R, X5R, X6S: $\geq 10\text{V}^{**}$, within $\pm 12.5\%$; $\leq 6.3\text{V}$ within $\pm 25\%$; TT series & $C \geq 1\mu\text{F}$, within $\pm 25\%$ **10V: $0603 \geq 4.7\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0201 \geq 0.1\mu\text{F}$, within $\pm 25\%$; Y5V: $\geq 10\text{V}$, within $\pm 30\%$; $\leq 6.3\text{V}$, within $+30/-40\%$ Q/D.F. value: NPO: $C \geq 30\text{pF}$, $Q \geq 200$; $C < 30\text{pF}$, $Q \geq 100+10/3\text{C}$ X7R, X5R, X6S: 			
			Rated vol.	D.F. \leq	Exception of D.F. \leq	
			$\geq 100\text{V}$	$\leq 3\%$	$\leq 6\%$ $1206 \geq 0.47\mu\text{F}$ $\leq 7.5\%$ $0805 \geq 0.1\mu\text{F}$, $0603 \geq 0.068\mu\text{F}$, $1206 > 1\mu\text{F}$; TT series	
			$\geq 50\text{V}$	$\leq 3\%$	$\leq 6\%$ $0201(50\text{V})$; $0603 \geq 0.047\mu\text{F}$; $0805 \geq 0.18\mu\text{F}$; $1206 \geq 0.47\mu\text{F}$ $\leq 10\%$ $1210 \geq 4.7\mu\text{F}$ $\leq 20\%$ $0402 \geq 0.1\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$; TT series	
			35V	$\leq 5\%$	$\leq 20\%$ $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$ $\leq 10\%$ $0201 \geq 0.01\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1210 \geq 10\mu\text{F}$ $\leq 14\%$ $0603 \geq 0.33\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$ $\leq 15\%$ $0402 \geq 0.10\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 6.8\mu\text{F}$; $1210 \geq 22\mu\text{F}$; TT series $\leq 20\%$ $0402 \geq 1\mu\text{F}$	
			25V	$\leq 5\%$	$\leq 10\%$ $0603 \geq 0.15\mu\text{F}$; $0805 \geq 0.68\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$ $\leq 15\%$ $0201 \geq 0.01\mu\text{F}$; $0402 \geq 0.033\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$; TT series	
			16V	$\leq 5\%$	$\leq 15\%$ $0201 \geq 0.012\mu\text{F}$; $0402 \geq 0.33\mu\text{F}$ ($0402/X7\text{R} \geq 0.22\mu\text{F}$); $0603 \geq 0.33\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 22\mu\text{F}$ $\leq 20\%$ $0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; TT series	
			10V	$\leq 7.5\%$	$\leq 15\%$ $0201 \geq 0.012\mu\text{F}$; $0402 \geq 0.33\mu\text{F}$ ($0402/X7\text{R} \geq 0.22\mu\text{F}$); $0603 \geq 0.33\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 2.2\mu\text{F}$; $1210 \geq 22\mu\text{F}$ $\leq 20\%$ $0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; TT series	
			6.3V	$\leq 15\%$	$\leq 30\%$ $0201 \geq 0.1\mu\text{F}$; $0402 \geq 1\mu\text{F}$; $0603 \geq 10\mu\text{F}$; $0805 \geq 4.7\mu\text{F}$; $1206 \geq 47\mu\text{F}$; $1210 \geq 100\mu\text{F}$; TT series	
			4V	$\leq 20\%$	---	---
			Y5V:			
			Rated vol.	D.F. \leq	Exception of D.F. \leq	
			$\geq 50\text{V}$	7.5%	10% $0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$	
			35V	10%	---	
			25V	7.5%	10% $0402 \geq 0.047\mu\text{F}$; $0603 \geq 0.1\mu\text{F}$; $0805 \geq 0.33\mu\text{F}$; $1206 \geq 1\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$ 15% $0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 22\mu\text{F}$	
			16V ($C < 1.0\mu\text{F}$)	10%	12.5% $0402 \geq 0.068\mu\text{F}$; $0603 \geq 0.68\mu\text{F}$ 20% $0402 \geq 0.22\mu\text{F}$	
			16V ($C \geq 1.0\mu\text{F}$)	12.5%	20% $0603 \geq 2.2\mu\text{F}$; $0805 \geq 3.3\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 22\mu\text{F}$; $1812 \geq 47\mu\text{F}$	
			10V	20%	30% $0402 \geq 0.47\mu\text{F}$	
			6.3V	30%	---	---
			*I.R. : $\geq 10\text{V}$, $500\text{M}\Omega$ or 25 Q-F whichever is smaller. Class II (X7R, X5R, X6S, Y5V)			
			Rated voltage	Insulation Resistance		
			100V: X7R	500MΩ or $R \times C \geq 5\text{ Q-F}$ whichever is smaller.		
			50V: $0402 \geq 0.1\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 1\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 4.7\mu\text{F}$			
			35V: $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1210 \geq 10\mu\text{F}$			
			25V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 2.2\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 10\mu\text{F}$			
			16V: $0201 \geq 0.1\mu\text{F}$; $0402 \geq 0.22\mu\text{F}$; $0603 \geq 1\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 10\mu\text{F}$; $1210 \geq 47\mu\text{F}$			
			10V: $0201 \geq 47\text{nF}$; $0402 \geq 0.47\mu\text{F}$; $0603 \geq 0.47\mu\text{F}$; $0805 \geq 2.2\mu\text{F}$; $1206 \geq 4.7\mu\text{F}$; $1210 \geq 47\mu\text{F}$			
			6.3V ; 4V ; TT series ; All X6S items			


No	Item	Test Condition				Requirements																																																																																																																																																								
15.	High Temperature Load (Endurance)	Test temp. : NP0, X7R/X7E: $125 \pm 3^\circ\text{C}$ X6S: $105 \pm 3^\circ\text{C}$ X5R, Y5V: $85 \pm 3^\circ\text{C}$ Test time: $1000 + 24/-0$ hrs. To apply voltage: (1) $\leq 6.3\text{V}$ or $C \geq 10\mu\text{F}$ or TT series: 150% of rated voltage. (2) $10\text{V} \leq U_r < 500\text{V}$: 200% of rated voltage. (3) 500V: 150% of rated voltage. (4) $U_r \geq 630\text{V}$: 120% of rated voltage. (5) 100% of rated voltage for below range.				* No remarkable damage. Cap change: NP0: $\pm 3.0\%$ or $\pm 0.3\mu\text{F}$ whichever is larger X7R, X5R, X6S: $\geq 10\text{V}^{**}$, within $\pm 12.5\%$; $\leq 6.3\text{V}$ within $\pm 25\%$; TT series & C2 1μF, within $\pm 25\%$ **10V: 0603 $\geq 4.7\mu\text{F}$; 0402 $\geq 1\mu\text{F}$; 0201 $\geq 0.1\mu\text{F}$, within $\pm 25\%$; Y5V: $\geq 10\text{V}$, within $\pm 30\%$; $\leq 6.3\text{V}$, within $+30/-40\%$ Q/D.F. value: NP0: More than $30\mu\text{F}$, $Q \geq 350$ $10\mu\text{F} \leq C < 30\mu\text{F}$, $Q \geq 275 \pm 2.5\text{C}$ Less than $10\mu\text{F}$, $Q \geq 200 \pm 10\text{C}$ X7R, X5R, X6S:																																																																																																																																																								
		<table border="1"> <thead> <tr> <th>Size</th><th>Dielectric</th><th>Rated voltage</th><th>Capacitance range</th></tr> </thead> <tbody> <tr> <td>0201</td><td>X5R/X7R/X6S</td><td>$\leq 10\text{V}$</td><td>$C \geq 0.1\mu\text{F}$</td></tr> <tr> <td>0402</td><td>X5R/X7R/X6S</td><td>$6.3\text{V}, 10\text{V}$</td><td>$C \geq 1.0\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>25V</td><td>$C \geq 22\mu\text{F}$</td></tr> <tr> <td>0603</td><td>X5R/X7R/X6S</td><td>$6.3\text{V}, 10\text{V}$</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$25\text{V}, 35\text{V}$</td><td>$C \geq 1.0\mu\text{F}$</td></tr> <tr> <td>0805</td><td>X5R/X7R/X6S</td><td>6.3V</td><td>$C \geq 47\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$10\text{V} - 50\text{V}$</td><td>$C \geq 22\mu\text{F}$</td></tr> <tr> <td>1206</td><td>X5R/X7R/X6S</td><td>6.3V</td><td>$C \geq 10\mu\text{F}$</td></tr> <tr> <td></td><td>NP0</td><td>3000V</td><td>$C \geq 47\mu\text{F}$</td></tr> <tr> <td>1210</td><td>X5R/X7R/X6S</td><td>16V</td><td>$C \geq 1.5\mu\text{F}$</td></tr> <tr> <td>TT18</td><td>Y5V</td><td>$6.3\text{V}, 10\text{V}$</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td>TT21</td><td>Y5V</td><td>6.3V</td><td>$C \geq 2.2\mu\text{F}$</td></tr> <tr> <td>TT31</td><td>Y5V</td><td>6.3V</td><td>$C \geq 10\mu\text{F}$</td></tr> <tr> <td></td><td></td><td></td><td>**1WV items must follow de-rating conditions</td></tr> <tr> <td></td><td></td><td></td><td>(6) 150% of rated voltage for below range.</td></tr> <tr> <td></td><td></td><td colspan="4"> <table border="1"> <thead> <tr> <th>Size</th><th>Dielectric</th><th>Rated voltage</th><th>Capacitance range</th></tr> </thead> <tbody> <tr> <td>0201</td><td>X5R/X7R/X6</td><td>$16\text{V}/25\text{V}$</td><td>$C \geq 0.1\mu\text{F}$</td></tr> <tr> <td>0402</td><td>X5R/X7R/X6</td><td>50V</td><td>$C \geq 0.1\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$10 - 25\text{V}$</td><td>$C \geq 0.22\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$Y5V$</td><td>$C \geq 0.47\mu\text{F}$</td></tr> <tr> <td>0603</td><td>X5R/X7R/X6</td><td>50V</td><td>$C > 0.1\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$10 - 50\text{V}$</td><td>$C \geq 1.0\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$Y5V$</td><td>$C \geq 2.2\mu\text{F}$</td></tr> <tr> <td>0805</td><td>X5R/X7R/X6</td><td>$10 - 50\text{V}$</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>50V</td><td>$C \geq 2.2\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$Y5V$</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td>1206</td><td>X5R/X7R/X6</td><td>100V</td><td>$C > 1.0\mu\text{F}$</td></tr> <tr> <td>2220</td><td>X7R</td><td>100V</td><td>$C \geq 6.8\mu\text{F}$</td></tr> </tbody> </table> </td></tr> <tr> <td></td><td></td><td colspan="4"> Before initial measurement (Class II only): To apply test voltage for 1hr at test temp. and then set for 24 ± 2 hrs at room temp. Measurement to be made after keeping at room temp. for 24 ± 2 hrs </td></tr> <tr> <td></td><td></td><td colspan="4"> ** De-rating conditions:  <p>The graph plots the ratio of operating voltage to rated voltage (%) against temperature in °C. Three lines are shown: Product for 125°C (steepest), Product for 105°C (middle), and Product for 85°C (shallowest). All lines show a linear decrease from approximately 100% at 0°C to about 60% at 150°C.</p> </td></tr> <tr> <td></td><td></td><td colspan="4"> *I.R.: $\geq 10\text{V}$, $1\text{G}\Omega$ or $50\text{ }\Omega\text{-F}$ whichever is smaller. Class II (X7R, X5R, X6S, Y5V) </td></tr> <tr> <td></td><td></td><td colspan="4"> <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: X7R</td> <td rowspan="7" style="vertical-align: middle;"> 1GΩ or $R_{XC} \geq 10\text{ }\Omega\text{-F}$ whichever is smaller. </td> </tr> <tr> <td>50V: 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$</td> </tr> <tr> <td>35V: 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$</td> </tr> <tr> <td>25V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 10\mu\text{F}$</td> </tr> <tr> <td>16V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 47\mu\text{F}$</td> </tr> <tr> <td>10V: 0201 $\geq 47\text{nF}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$</td> </tr> <tr> <td>6.3V ; 4V ; TT series ; All X6S items</td> </tr> </tbody> </table> </td></tr> </tbody> </table>	Size	Dielectric	Rated voltage	Capacitance range	0201	X5R/X7R/X6S	$\leq 10\text{V}$	$C \geq 0.1\mu\text{F}$	0402	X5R/X7R/X6S	$6.3\text{V}, 10\text{V}$	$C \geq 1.0\mu\text{F}$			25V	$C \geq 22\mu\text{F}$	0603	X5R/X7R/X6S	$6.3\text{V}, 10\text{V}$	$C \geq 4.7\mu\text{F}$			$25\text{V}, 35\text{V}$	$C \geq 1.0\mu\text{F}$	0805	X5R/X7R/X6S	6.3V	$C \geq 47\mu\text{F}$			$10\text{V} - 50\text{V}$	$C \geq 22\mu\text{F}$	1206	X5R/X7R/X6S	6.3V	$C \geq 10\mu\text{F}$		NP0	3000V	$C \geq 47\mu\text{F}$	1210	X5R/X7R/X6S	16V	$C \geq 1.5\mu\text{F}$	TT18	Y5V	$6.3\text{V}, 10\text{V}$	$C \geq 4.7\mu\text{F}$	TT21	Y5V	6.3V	$C \geq 2.2\mu\text{F}$	TT31	Y5V	6.3V	$C \geq 10\mu\text{F}$				**1WV items must follow de-rating conditions				(6) 150% of rated voltage for below range.			<table border="1"> <thead> <tr> <th>Size</th><th>Dielectric</th><th>Rated voltage</th><th>Capacitance range</th></tr> </thead> <tbody> <tr> <td>0201</td><td>X5R/X7R/X6</td><td>$16\text{V}/25\text{V}$</td><td>$C \geq 0.1\mu\text{F}$</td></tr> <tr> <td>0402</td><td>X5R/X7R/X6</td><td>50V</td><td>$C \geq 0.1\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$10 - 25\text{V}$</td><td>$C \geq 0.22\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$Y5V$</td><td>$C \geq 0.47\mu\text{F}$</td></tr> <tr> <td>0603</td><td>X5R/X7R/X6</td><td>50V</td><td>$C > 0.1\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$10 - 50\text{V}$</td><td>$C \geq 1.0\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$Y5V$</td><td>$C \geq 2.2\mu\text{F}$</td></tr> <tr> <td>0805</td><td>X5R/X7R/X6</td><td>$10 - 50\text{V}$</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>50V</td><td>$C \geq 2.2\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$Y5V$</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td>1206</td><td>X5R/X7R/X6</td><td>100V</td><td>$C > 1.0\mu\text{F}$</td></tr> <tr> <td>2220</td><td>X7R</td><td>100V</td><td>$C \geq 6.8\mu\text{F}$</td></tr> </tbody> </table>				Size	Dielectric	Rated voltage	Capacitance range	0201	X5R/X7R/X6	$16\text{V}/25\text{V}$	$C \geq 0.1\mu\text{F}$	0402	X5R/X7R/X6	50V	$C \geq 0.1\mu\text{F}$			$10 - 25\text{V}$	$C \geq 0.22\mu\text{F}$			$Y5V$	$C \geq 0.47\mu\text{F}$	0603	X5R/X7R/X6	50V	$C > 0.1\mu\text{F}$			$10 - 50\text{V}$	$C \geq 1.0\mu\text{F}$			$Y5V$	$C \geq 2.2\mu\text{F}$	0805	X5R/X7R/X6	$10 - 50\text{V}$	$C \geq 4.7\mu\text{F}$			50V	$C \geq 2.2\mu\text{F}$			$Y5V$	$C \geq 4.7\mu\text{F}$	1206	X5R/X7R/X6	100V	$C > 1.0\mu\text{F}$	2220	X7R	100V	$C \geq 6.8\mu\text{F}$			Before initial measurement (Class II only): To apply test voltage for 1hr at test temp. and then set for 24 ± 2 hrs at room temp. Measurement to be made after keeping at room temp. for 24 ± 2 hrs						** De-rating conditions:  <p>The graph plots the ratio of operating voltage to rated voltage (%) against temperature in °C. Three lines are shown: Product for 125°C (steepest), Product for 105°C (middle), and Product for 85°C (shallowest). All lines show a linear decrease from approximately 100% at 0°C to about 60% at 150°C.</p>						*I.R.: $\geq 10\text{V}$, $1\text{G}\Omega$ or $50\text{ }\Omega\text{-F}$ whichever is smaller. Class II (X7R, X5R, X6S, Y5V)						<table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: X7R</td> <td rowspan="7" style="vertical-align: middle;"> 1GΩ or $R_{XC} \geq 10\text{ }\Omega\text{-F}$ whichever is smaller. </td> </tr> <tr> <td>50V: 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$</td> </tr> <tr> <td>35V: 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$</td> </tr> <tr> <td>25V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 10\mu\text{F}$</td> </tr> <tr> <td>16V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 47\mu\text{F}$</td> </tr> <tr> <td>10V: 0201 $\geq 47\text{nF}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$</td> </tr> <tr> <td>6.3V ; 4V ; TT series ; All X6S items</td> </tr> </tbody> </table>				Rated voltage	Insulation Resistance	100V: X7R	1GΩ or $R_{XC} \geq 10\text{ }\Omega\text{-F}$ whichever is smaller.	50V: 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$	35V: 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$	25V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 10\mu\text{F}$	16V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 47\mu\text{F}$	10V: 0201 $\geq 47\text{nF}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$	6.3V ; 4V ; TT series ; All X6S items
Size	Dielectric	Rated voltage	Capacitance range																																																																																																																																																											
0201	X5R/X7R/X6S	$\leq 10\text{V}$	$C \geq 0.1\mu\text{F}$																																																																																																																																																											
0402	X5R/X7R/X6S	$6.3\text{V}, 10\text{V}$	$C \geq 1.0\mu\text{F}$																																																																																																																																																											
		25V	$C \geq 22\mu\text{F}$																																																																																																																																																											
0603	X5R/X7R/X6S	$6.3\text{V}, 10\text{V}$	$C \geq 4.7\mu\text{F}$																																																																																																																																																											
		$25\text{V}, 35\text{V}$	$C \geq 1.0\mu\text{F}$																																																																																																																																																											
0805	X5R/X7R/X6S	6.3V	$C \geq 47\mu\text{F}$																																																																																																																																																											
		$10\text{V} - 50\text{V}$	$C \geq 22\mu\text{F}$																																																																																																																																																											
1206	X5R/X7R/X6S	6.3V	$C \geq 10\mu\text{F}$																																																																																																																																																											
	NP0	3000V	$C \geq 47\mu\text{F}$																																																																																																																																																											
1210	X5R/X7R/X6S	16V	$C \geq 1.5\mu\text{F}$																																																																																																																																																											
TT18	Y5V	$6.3\text{V}, 10\text{V}$	$C \geq 4.7\mu\text{F}$																																																																																																																																																											
TT21	Y5V	6.3V	$C \geq 2.2\mu\text{F}$																																																																																																																																																											
TT31	Y5V	6.3V	$C \geq 10\mu\text{F}$																																																																																																																																																											
			**1WV items must follow de-rating conditions																																																																																																																																																											
			(6) 150% of rated voltage for below range.																																																																																																																																																											
		<table border="1"> <thead> <tr> <th>Size</th><th>Dielectric</th><th>Rated voltage</th><th>Capacitance range</th></tr> </thead> <tbody> <tr> <td>0201</td><td>X5R/X7R/X6</td><td>$16\text{V}/25\text{V}$</td><td>$C \geq 0.1\mu\text{F}$</td></tr> <tr> <td>0402</td><td>X5R/X7R/X6</td><td>50V</td><td>$C \geq 0.1\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$10 - 25\text{V}$</td><td>$C \geq 0.22\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$Y5V$</td><td>$C \geq 0.47\mu\text{F}$</td></tr> <tr> <td>0603</td><td>X5R/X7R/X6</td><td>50V</td><td>$C > 0.1\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$10 - 50\text{V}$</td><td>$C \geq 1.0\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$Y5V$</td><td>$C \geq 2.2\mu\text{F}$</td></tr> <tr> <td>0805</td><td>X5R/X7R/X6</td><td>$10 - 50\text{V}$</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>50V</td><td>$C \geq 2.2\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>$Y5V$</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td>1206</td><td>X5R/X7R/X6</td><td>100V</td><td>$C > 1.0\mu\text{F}$</td></tr> <tr> <td>2220</td><td>X7R</td><td>100V</td><td>$C \geq 6.8\mu\text{F}$</td></tr> </tbody> </table>				Size	Dielectric	Rated voltage	Capacitance range	0201	X5R/X7R/X6	$16\text{V}/25\text{V}$	$C \geq 0.1\mu\text{F}$	0402	X5R/X7R/X6	50V	$C \geq 0.1\mu\text{F}$			$10 - 25\text{V}$	$C \geq 0.22\mu\text{F}$			$Y5V$	$C \geq 0.47\mu\text{F}$	0603	X5R/X7R/X6	50V	$C > 0.1\mu\text{F}$			$10 - 50\text{V}$	$C \geq 1.0\mu\text{F}$			$Y5V$	$C \geq 2.2\mu\text{F}$	0805	X5R/X7R/X6	$10 - 50\text{V}$	$C \geq 4.7\mu\text{F}$			50V	$C \geq 2.2\mu\text{F}$			$Y5V$	$C \geq 4.7\mu\text{F}$	1206	X5R/X7R/X6	100V	$C > 1.0\mu\text{F}$	2220	X7R	100V	$C \geq 6.8\mu\text{F}$																																																																																																					
Size	Dielectric	Rated voltage	Capacitance range																																																																																																																																																											
0201	X5R/X7R/X6	$16\text{V}/25\text{V}$	$C \geq 0.1\mu\text{F}$																																																																																																																																																											
0402	X5R/X7R/X6	50V	$C \geq 0.1\mu\text{F}$																																																																																																																																																											
		$10 - 25\text{V}$	$C \geq 0.22\mu\text{F}$																																																																																																																																																											
		$Y5V$	$C \geq 0.47\mu\text{F}$																																																																																																																																																											
0603	X5R/X7R/X6	50V	$C > 0.1\mu\text{F}$																																																																																																																																																											
		$10 - 50\text{V}$	$C \geq 1.0\mu\text{F}$																																																																																																																																																											
		$Y5V$	$C \geq 2.2\mu\text{F}$																																																																																																																																																											
0805	X5R/X7R/X6	$10 - 50\text{V}$	$C \geq 4.7\mu\text{F}$																																																																																																																																																											
		50V	$C \geq 2.2\mu\text{F}$																																																																																																																																																											
		$Y5V$	$C \geq 4.7\mu\text{F}$																																																																																																																																																											
1206	X5R/X7R/X6	100V	$C > 1.0\mu\text{F}$																																																																																																																																																											
2220	X7R	100V	$C \geq 6.8\mu\text{F}$																																																																																																																																																											
		Before initial measurement (Class II only): To apply test voltage for 1hr at test temp. and then set for 24 ± 2 hrs at room temp. Measurement to be made after keeping at room temp. for 24 ± 2 hrs																																																																																																																																																												
		** De-rating conditions:  <p>The graph plots the ratio of operating voltage to rated voltage (%) against temperature in °C. Three lines are shown: Product for 125°C (steepest), Product for 105°C (middle), and Product for 85°C (shallowest). All lines show a linear decrease from approximately 100% at 0°C to about 60% at 150°C.</p>																																																																																																																																																												
		*I.R.: $\geq 10\text{V}$, $1\text{G}\Omega$ or $50\text{ }\Omega\text{-F}$ whichever is smaller. Class II (X7R, X5R, X6S, Y5V)																																																																																																																																																												
		<table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: X7R</td> <td rowspan="7" style="vertical-align: middle;"> 1GΩ or $R_{XC} \geq 10\text{ }\Omega\text{-F}$ whichever is smaller. </td> </tr> <tr> <td>50V: 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$</td> </tr> <tr> <td>35V: 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$</td> </tr> <tr> <td>25V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 10\mu\text{F}$</td> </tr> <tr> <td>16V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 47\mu\text{F}$</td> </tr> <tr> <td>10V: 0201 $\geq 47\text{nF}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$</td> </tr> <tr> <td>6.3V ; 4V ; TT series ; All X6S items</td> </tr> </tbody> </table>				Rated voltage	Insulation Resistance	100V: X7R	1GΩ or $R_{XC} \geq 10\text{ }\Omega\text{-F}$ whichever is smaller.	50V: 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$	35V: 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$	25V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 10\mu\text{F}$	16V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 47\mu\text{F}$	10V: 0201 $\geq 47\text{nF}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$	6.3V ; 4V ; TT series ; All X6S items																																																																																																																																															
Rated voltage	Insulation Resistance																																																																																																																																																													
100V: X7R	1GΩ or $R_{XC} \geq 10\text{ }\Omega\text{-F}$ whichever is smaller.																																																																																																																																																													
50V: 0402 $\geq 0.1\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 1\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 4.7\mu\text{F}$																																																																																																																																																														
35V: 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1210 $\geq 10\mu\text{F}$																																																																																																																																																														
25V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 2.2\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 10\mu\text{F}$																																																																																																																																																														
16V: 0201 $\geq 0.1\mu\text{F}$; 0402 $\geq 0.22\mu\text{F}$; 0603 $\geq 1\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 10\mu\text{F}$; 1210 $\geq 47\mu\text{F}$																																																																																																																																																														
10V: 0201 $\geq 47\text{nF}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$																																																																																																																																																														
6.3V ; 4V ; TT series ; All X6S items																																																																																																																																																														

APPENDIXES

□ Tape & reel dimensions




Size	0201	0402		0603	0805			1206			1210			1812		
Thickness	L	N	E	S, X	A, H	B, T	C, D, I	B, T	C, J, D	G,P	C, D	F, G, K	M	D, F, G, K	M	U
A₀	0.38±0.05	0.62±0.05	0.70±0.10	1.02±0.05	1.50±0.10	1.50±0.10	<1.57	2.00±0.10	<1.85	<1.95	<2.97	<2.97	<2.97	<3.81	<3.81	<3.90
B₀	0.68±0.05	1.12±0.05	1.20±0.10	1.80±0.05	2.30±0.10	2.30±0.10	<2.40	3.50±0.10	<3.46	<3.67	<3.73	<3.73	<3.73	<5.30	<5.30	<5.30
T	0.42±0.05	0.60±0.05	0.70±0.10	0.95±0.05	0.75±0.05	0.95±0.05	0.23±0.05	0.95±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.25±0.05	0.25±0.05	0.25±0.05
K₀	-	-	-	-	-	-	<2.50	-	<2.50	<2.50	<2.50	<2.50	<2.50	<3.00	<2.50	<3.50
W	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	12.0±0.20	12.0±0.20	12.0±0.20
P₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP₀	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.20
P₁	2.00±0.05	2.00±0.05	2.00±0.05	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10
P₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D₀	1.55±0.05	1.55±0.05	1.55±0.05	1.55±0.05	1.55±0.05	1.55±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.10
D₁	-	-	-	-	-	-	1.00±0.10	-	1.00±0.10	1.00±0.10	1.00±0.10	1.00±0.10	1.00±0.10	1.50±0.10	1.50±0.10	1.50±0.10
E	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05



Size	0201, 0402, 0603, 0805, 1206, 1210			1812
Reel size	7"	10"	13"	7"
C	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2
W₁	8.4+1.5/-0	8.4+1.5/-0	8.4+1.5/-0	12.4+2.0/-0
A	178.0±0.10	250.0±1.0	330.0±1.0	178.0±0.10
N	60.0+1.0/-0	100.0±1.0	100±1.0	60.0+1.0/-0

□ Description of customer label



- a. Customer name
- b. WTC order series and item number
- c. Customer P/O
- d. Customer P/N
- e. Description of product
- f. Quantity
- g. Bar code including quantity & WTC P/N or customer
- h. WTC P/N
- i. Shipping date
- j. Order bar code including series and item numbers
- k. Serial number of label

□ Constructions

No.	Name	NPO, X7R, X5R, X6S, Y5V
①	Ceramic material	BaTiO ₃ based
②	Inner electrode	Ni
③	Termination	Inner layer
④		Middle layer
⑤		Outer layer




Fig. 5 The construction of MLCC

□ Storage and handling conditions

- (1) To store products at 5 to 40°C ambient temperature and 20 to 70%. related humidity conditions.
- (2) The product is recommended to be used within one year after shipment. Check solderability in case of shelf life extension is needed.

Cautions:

- The corrosive gas reacts on the terminal electrodes of capacitors, and results in the poor solderability. Do not store the capacitors in the ambience of corrosive gas (e.g., hydrogen sulfide, sulfur dioxide, chlorine, ammonia gas etc.)
- In corrosive atmosphere, solderability might be degraded, and silver migration might occur to cause low reliability.
- Due to the dewing by rapid humidity change, or the photochemical change of the terminal electrode by direct sunlight, the solderability and electrical performance may deteriorate. Do not store capacitors under direct sunlight or dewing condition. To store products on the shelf and avoid exposure to moisture.

□ Recommended soldering conditions

The lead-free termination MLCCs are not only to be used on SMT against lead-free solder paste, but also suitable against lead-containing solder paste. If the optimized solder joint is requested, increasing soldering time, temperature and concentration of N₂ within oven are recommended.




Fig. 6 Recommended reflow soldering profile for SMT process with SnAgCu series solder paste.




Fig. 7 Recommended wave soldering profile for SMT process with SnAgCu series solder.